



Quality Paints since 1845
MATHYS®



DIVALO

Varnish for the finishing touch of interior wall paints.

- Not yellowing
- Smooth satin views
- Washable

DIVALO

POPIS PRODUKTU (DLHÝ)

Water based acrylic varnish. For the finishing touch of interior wall paints when a high mechanical resistance is required.

ODPORÚČANÉ POUŽITIE

Finish on indoor paints and decorative paint systems when a high mechanical resistance is required. Recommended as a topcoat on decorative paint systems (Fair-Decor).

TECHNICAL DATA

Hustota (g/cm ³):	1,02 - 1,06
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	Satin Gloss: ± 20%
Obsah pevných látok v hmotnosti:	30 - 33 %
Obsah pevných látok v objeme:	27,5 - 30,5 %

DRY TIMES BY 20

Na dotyk suché:	30 minutes
Suchý na opätovné natieranie:	4 hours
Úplne vytvrdené:	± 1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

± 70 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

± 20 µm

TEORETICKÁ SPOTREBA

12 - 14 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Clean and degrease substrate. The paint coats or systems that have to be protected have to be dry and/or fully cured.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

> 5°C, max. 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply in 1 or 2 coats with flat brush. If necessary dilute with water.

APLIKÁCIA A RIEDENIE: VALEC

Apply in 1 or 2 coats with lacquer. If necessary dilute with water.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 09 - 013 / Pressure: 180 bars.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

If necessary dilute with water.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

DATA SAFETY DATA

Úroveň VOC:	90 g/l
VOC readymix:	90 g/l
Kategória VOC:	A/e
Limit VOC:	130 g/l
Grenelle:	A+
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu