

Quality Paints since 1845
MATHYS[®]



DURBOCEM[®]

Coating for humid inner and outer walls and cellars

- Builds a strong bond with the damp substrate
- Can be applied on chalking substrates
- Builds a strong bond with cement-based substrates
- Contains cement, and therefore this product is extremely suitable to be applied on damp substrates
- Can be recoated with Paracem[®] (when the substrate is dry)

WWW.MATHYSPAINTS.EU

DURBOCEM®

POPIS PRODUKTU (DLOUHÝ)

A solvent-based paint based on plasticized acrylic resins for inside and outside use. It renews walls damaged by water and protects new walls against damp damage.

DOPORUČENÉ POUŽITÍ

Painting of damp walls and cellars.

TECHNICAL_DATA

Hustota (g/cm ³):	1,24 - 1,28
Úroveň lesku:	Matt
Úroveň lesku při 60°:	Matt: 2%
Obsah pevných látek v hmotnosti:	61 - 63 %
Obsah pevných látek v objemu:	28 - 40 %

DRY_TIMES_BY_20

Dotykem suché:	2 hours
Suché na manipulaci:	2 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	24 hours

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

500 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

200 µm

TEORETICKÁ SPOTŘEBA

1,5 - 3 m²/l (total consumption, 2 coats)

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

Brush off chalking surfaces with a wire brush. Water infiltration leaks must be made watertight with special quick cement by using a hawk or trowel. Let it harden.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating material should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Work in a well-ventilated area. > 5°C, < 80% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Use a semi-hard brush. Do not dilute.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Use a mohair roller. Do not dilute.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Not recommended.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit.

POZNÁMKY

- 1st coat: impregnate substrate using a semi-brush; walls in bad condition must be treated saturation. 2nd coat: finish after 24 hours with brush
- Since it concerns specific applications (e.g. caves), there has to be excellent ventilation, during the first weeks after application.
- Durbocem does not stop saltpetre efflorescence, does not resist against underground water pressure and therefore it cannot be considered as a waterproofing product.

DATA SAFETY DATA

Úroveň těkavých organických

látek: 500 g/L

VOC ready mix: 500 g/l

Kategorie VOC: A/i

Limitní hodnota VOC: 500 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu