

Quality Paints since 1845
MATHYS[®]



DURBOCEM[®]

Coating for humid inner and outer walls and cellars

- Builds a strong bond with the damp substrate
- Can be applied on chalking substrates
- Builds a strong bond with cement-based substrates
- Contains cement, and therefore this product is extremely suitable to be applied on damp substrates
- Can be recoated with Paracem[®] (when the substrate is dry)

DURBOCEM®

BESKRIVELSE

A solvent-based paint based on plasticized acrylic resins for inside and outside use. It renews walls damaged by water and protects new walls against damp damage.

ANBEFALT BRUK

Painting of damp walls and cellars.

TEKNISKE DATA

Tetthet:	1,24 - 1,28
Glansgrad:	Matt
Glansgrad ved 60°:	Matt: 2%
Tørrstoffinnhold i vekt:	61 - 63 %
Tørrstoffinnhold i volum:	28 - 40 %

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	2 hours
Håndterbar:	2 hours
Overmalbar:	24 hours
Herdetid:	24 hours

ANBEFALT VÅTFILMTYKKELSE

500 µm

ANBEFALT TØRRFILMTYKKELSE

200 µm

TEORETISK FORBRUK

1,5 - 3 m²/l (total consumption, 2 coats)

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Brush off chalking surfaces with a wire brush. Water infiltration leaks must be made watertight with special quick cement by using a hawk or trowel. Let it harden.

BRUKSANVISNING

To ensure homogeneity, coating material should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Work in a well-ventilated area. > 5°C, < 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

Use a semi-hard brush. Do not dilute.

PÅFØRING & FORTYNNING: RULLE

Use a mohair roller. Do not dilute.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Not recommended.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Not recommended.

RENGJØRING AV UTSTYR/SPILL

White spirit.

MERKNADER

- 1st coat: impregnate substrate using a semi-brush; walls in bad condition must be treated saturation. 2nd coat: finish after 24 hours with brush
- Since it concerns specific applications (e.g. caves), there has to be excellent ventilation, during the first weeks after application.
- Durbocem does not stop saltpetre efflorescence, does not resist against underground water pressure and therefore it cannot be considered as a waterproofing product.

SIKKERHETSDATA

VOC nivå:	500 g/L
VOC ferdigblandet:	500 g/l
VOC kategori:	A/i
VOC grense:	500 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu