

Quality Paints since 1845
MATHYS[®]



DURBOCEM[®]

Coating for humid inner and outer walls and cellars

- Builds a strong bond with the damp substrate
- Can be applied on chalking substrates
- Builds a strong bond with cement-based substrates
- Contains cement, and therefore this product is extremely suitable to be applied on damp substrates
- Can be recoated with Paracem[®] (when the substrate is dry)

WWW.MATHYSPAINTS.EU

DURBOCEM®

BESKRIVNING

A solvent-based paint based on plasticized acrylic resins for inside and outside use. It renews walls damaged by water and protects new walls against damp damage.

REKOMMENDERAD ANVÄNDNING

Painting of damp walls and cellars.

TEKNISK DATA

Densitet:	1,24 - 1,28
Glansnivå:	Matt
Glansnivå vid 60°:	Matt: 2%
Torrsubstansvikt:	61 - 63 %
Torrsubstansvolym:	28 - 40 %

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	2 hours
Hanteringstorr:	2 hours
Övermålningsbar:	24 hours
Fullt härdad:	24 hours

REKOMMENDERAD VÅTFILMSTJOCKLEK

500 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

200 µm

TEORETISK FÖRBRUKNING

1,5 - 3 m²/l (total consumption, 2 coats)

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

Brush off chalking surfaces with a wire brush. Water infiltration leaks must be made watertight with special quick cement by using a hawk or trowel. Let it harden.

BRUKSANVISNING

To ensure homogeneity, coating material should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Work in a well-ventilated area. > 5°C, < 80% R.H.

APPLICERING OCH SPÄDNING: PENSEL

Use a semi-hard brush. Do not dilute.

APPLICERING OCH SPÄDNING: ROLLER

Use a mohair roller. Do not dilute.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Not recommended.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Not recommended.

RENGÖRING AV UTRUSTNING/SPILL

White spirit.

ANMÄRKNINGAR

- 1st coat: impregnate substrate using a semi-brush; walls in bad condition must be treated saturation. 2nd coat: finish after 24 hours with brush
- Since it concerns specific applications (e.g. caves), there has to be excellent ventilation, during the first weeks after application.
- Durbocem does not stop saltpetre efflorescence, does not resist against underground water pressure and therefore it cannot be considered as a waterproofing product.

SÄKERHETSDATA

VOC-nivå:	500 g/L
VOC färdigmix:	500 g/l
VOC-kategori:	A/i
VOC-gräns:	500 g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskadorna. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europas rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu