

Quality Paints since 1845  
**MATHYS®**



## ELASTOFILL®

### Elastic jointing paste based on acrylic dispersions

- Forms a rubberlike mass with permanently high elasticity (> 900%) after evaporation of the water
- Can absorb strong expansions and deformations
- Alkali resistant
- Very resistant to ageing
- Waterproof

# ELASTOFILL®

## BESKRIVNING

An elastic, paintable jointing paste based on acrylic dispersions for sealing, jointing, filling. For inside use.

## REKOMMENDERAD ANVÄNDNING

Sealing, jointing, filling, fixing, glueing on concrete, wood, metal, glass, hard PVC, tiles, plaster, alu-bitumen, etc.

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr: 3 hours, film thickness 8 mm  
Hanteringstorr: 8 hours, film thickness 8 mm  
Övermålningsbar: 1 day, film thickness 8 mm  
Fullt härdad: ± 1 week, film thickness 8 mm

## TEORETISK FÖRBRUKNING

For a joint of 10 mm wide and 15 mm deep: ± 6 meters run.  
Jointing paste has to be applied in maximum 10 mm wet film thickness.

## PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## YTFÖRBEREDELSE

Grind out fine cracks in V-shape till about 0,5 cm wide; if depth > 1/2 x width, apply a back filling. The crack edges must be primed with Parafix, Pegafix or Vernac (diluted with Thinner 22). Hard PVC is to be primed with Primer 44 HS, metal and glass with diluted Noxyde.

## BRUKSANVISNING

Manual spray gun (nozzle free to choose) - spatula, palette knife, glue spreader (combed lime fills ± 3 mm thick).

## APPLICERINGSFÖRHÅLLANDEN

> 5°C, Max. R.H. 80%

## RENGÖRING AV UTRUSTNING/SPILL

Water. After drying Elastofill can only be removed mechanically or softened with a synthetic thinner; then remove by rubbing or scratching.

## ANMÄRKNINGAR

Joints have to be smoothed with a finger or with a cloth soaked in Thinner 22 or in water (+ soap).

The surface in contact with the air must be sufficiently large, since Elastofill is to be transformed into a rubber like mass by evaporation of the water.

On porous surfaces, always use an appropriate primer.

Elastofill can be recoated with the following paints: acrylic paints Murfill, Paracem (Elastofill has to be isolated first with Porisol), Paracem Semi-Gloss, Pegacryl, Pegacryl Satin, with high and satin gloss alkyd enamels, with Porisol and Pegatex.

## SÄKERHETSDATA

VOC-gräns: 5 g/l  
Anmärkningar om säkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utgivet den: 07/02/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)