

Quality Paints since 1845
MATHYS[®]



ELASTOPRO

Plasto-elastic sealant for inside and outside use

- For inside and outside use
- Sealing and finishing of joints and cracks
- Quick paintable
- Shrinks hardly
- Excellent adhesion

ELASTOPRO

BESKRIVELSE

ElastoPro is based on an acrylic dispersion. The product is suitable for sealing connecting joints, cracks and joints.

ANBEFALT BRUK

Connecting joints between frames and masonry, stucco and gypsum board with moderate movement. Repairing and sealing cracks and joints in cellular concrete, stone plaster and wood. Not suitable for dilatation cracks.

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Overmalbar: After skin formation (> 20 minutes)
Herdetid: 1 to 2 weeks, depending on temperature, air humidity and joint width.

TEORETISK FORBRUK

± 12 running meters for a joint of 5 x 5 mm.

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

The surface must be clean, dust and oil-free. It is advisable to prime sensitive and mineral substrates in order to achieve a better adhesion.

BRUKSANVISNING

Joint building:

Fix joints with PE or PU to the correct depth.

Minimum joint width; 5 mm, maximum joint width 25 mm.

To prevent damage use only blunt and smooth spatulas. In case of joints with a rigid substrate use a polyethylene film to prevent three-point attachment.

Unsuitable are joints containing oil, tar, bitumen, natural rubber, EPDM or Chloroprene.

Joint finishing:

In order to achieve a smooth optical finish we advise to tape the edges with a suitable tape.

Apply ElastoPro without air confined in the joint. Completely fill the joint. Remove all unnecessary kit with a suitable spatula. Finish the joint by spraying a little water on the joint (add no smoothing additive to the water). To prevent damage later on, remove the tape around the edges.

PÅFØRINGSBETINGELSER

Application temperature +5°C to +25°C.

Protect ElastoPro during the curing process against frost.

Low temperatures will slow down the curing process.

RENGJØRING AV UTSTYR/SPILL

Water. After drying ElastoPro can only be removed mechanically.

MERKNADER

ElastoPro is recoatable with dispersion and alkyd coatings (testing before application is advisable). In case of static joints with small movement (max. 5%) ElastoPro can be coated after complete hardening. Recoating with high filled dispersion coats can give cracking in the layer.

ElastoPro is not suitable for seals between glass, glazed surfaces and joints with standing water.

ElastoPro is available in 310 ml cartridges.

HOLDBARHET

Minimum of 12 months from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukeren er selv ansvarlig for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatablad er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu