

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## ELASTOPRO

# Plasto-elastic sealant for inside and outside use

- For inside and outside use
- Sealing and finishing of joints and cracks
- Quick paintable
- Shrinks hardly
- Excellent adhesion

# ELASTOPRO

## BESKRIVNING

ElastoPro is based on an acrylic dispersion. The product is suitable for sealing connecting joints, cracks and joints.

## REKOMMENDERAD ANVÄNDNING

Connecting joints between frames and masonry, stucco and gypsum board with moderate movement. Repairing and sealing cracks and joints in cellular concrete, stone plaster and wood. Not suitable for dilatation cracks.

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Övermålningsbar: After skin formation (> 20 minutes)  
Fullt härdad: 1 to 2 weeks, depending on temperature, air humidity and joint width.

## TEORETISK FÖRBRUKNING

± 12 running meters for a joint of 5 x 5 mm.

## PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## YTFÖRBEREDELSE

The surface must be clean, dust and oil-free. It is advisable to prime sensitive and mineral substrates in order to achieve a better adhesion.

## BRUKSANVISNING

Joint building:

Fix joints with PE or PU to the correct depth.

Minimum joint width; 5 mm, maximum joint width 25 mm.

To prevent damage use only blunt and smooth spatulas. In case of joints with a rigid substrate use a polyethylene film to prevent three-point attachment.

Unsuitable are joints containing oil, tar, bitumen, natural rubber, EPDM or Chloroprene.

Joint finishing:

In order to achieve a smooth optical finish we advise to tape the edges with a suitable tape.

Apply Elastopro without air confined in the joint. Completely fill the joint. Remove all unnecessary kit with a suitable spatula. Finish the joint by spraying a little water on the joint (add no smoothing additive to the water). To prevent damage later on, remove the tape around the edges.

## APPLICERINGSFÖRHÅLLANDEN

Application temperature +5°C to +25°C.

Protect ElastoPro during the curing process against frost.

Low temperatures will slow down the curing process.

## RENGÖRING AV UTRUSTNING/SPILL

Water. After drying ElastoPro can only be removed mechanically.

## ANMÄRKNINGAR

ElastoPro is recoatable with dispersion and alkyd coatings (testing before application is advisable). In case of static joints with small movement (max. 5%) ElastoPro can be coated after complete hardening. Recoating with high filled dispersion coats can give cracking in the layer.

ElastoPro is not suitable for seals between glass, glazed surfaces and joints with standing water.

ElastoPro is available in 310 ml cartridges.

## HÅLLBARHET

Minimum of 12 months from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

### Rust-Oleum Netherlands B.V.

Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

### Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

### Rust-Oleum France S.A.S.

38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

### N.V. Martin Mathys S.A.

Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)