

Quality Paints since 1845
MATHYS[®]



FAIRTEX[®]

Matt paint for interior walls and ceilings

- Smooth and completely splash-free roller application
- Covers on porous and non porous substrates in 2 coats without gloss differences
- Uniform matt finish without turning
- Odorless
- High whiteness

POPIS PRODUKTU (DLOUHÝ)

Matt acrylic paint for interior walls and ceilings and can be applied on most surfaces.

DOPORUČENÉ POUŽITÍ

Inner decoration on most common substrates such as plaster, bricks and concrete. Also old paint coats in good condition and most wallpaper can be recoated with Fairtex

TECHNICAL_DATA

Hustota (g/cm ³):	1,38 - 1,41
Úroveň lesku:	Matt
Úroveň lesku při 85°:	1-2%
Obsah pevných látek v hmotnosti:	48 - 51 %
Obsah pevných látek v objemu:	28 - 32 %
Odolnost proti drhnutí za mokra (EN 13300):	wsr_c2

DRY_TIMES_BY_20

Dotykem suché:	30 minutes
Suché na manipulaci:	Not applicable
Suchý nátěr:	3 hours
Plně vytvrzené:	1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

140 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

45 µm

TEORETICKÁ SPOTŘEBA

6 - 8 m²/l

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

Always work on a dry stable substrate. On porous substrates, no specific pre-treatment is required in most cases. Slightly chalking substrates or new plaster should first be impregnated with Pegafix or, for very fast recoating on all substrates, with Zinsser primers Bulls Eye 123 or 123 Plus. Water or nicotine stains should be isolated with Pegamat RL or Pegamat Aqua Isole, or with Zinsser primers Bulls Eye 123, 123 Plus, or B-I-N.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Apply at a temperature of minimum 5°C and a R.H. of max. 80%

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

If necessary, dilute with 2-5% volume of water. Nozzle : 016-018 / Pressure 200 bars.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water

DATA_SAFETY_DATA

VOC readymix:	30 g/l
Kategorie VOC:	A/a
Limitní hodnota VOC:	30 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35 C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu