

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



**FASSICOAT<sup>®</sup>**

## Single paint system

- Moisture-regulating paint
- Serves at the same time as primer, surfacer and finish
- Excellent weather resistance

# FASSICOAT®

## POPIS PRODUKTU (DLHÝ)

Satin gloss single paint system based on alkyd resins for woodwork.

## ODPORÚČANÉ POUŽITIE

Painting of woodwork.

## ODPORÚČANÝ SYSTÉM

Serves at the same time as primer, surfacer and finish - moisture-regulating paint - excellent weather resistance.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,33 - 1,38
Úroveň lesku:	Satin
Obsah pevných látok v hmotnosti:	69 - 73 %
Obsah pevných látok v objeme:	51 - 56 %

## DRY TIMES BY 20

Na dotyk suché:	3 - 4 hours
Suché na manipuláciu:	5 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdnuté:	1 week

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

55 µm

## TEORETICKÁ SPOTREBA

10 - 15 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

Fassicoat serves as primer, surfacer and finish. Therefore, it is not necessary to use a special primer. In case of application on new and non-treated wood, if necessary, dilute the first coat with ± 3% volume of white spirit. In case of jointing, use Plastopan Super or Pegaflex by preference.

Poor quality wood: user primer FassiForce. Do not apply Fassicoat directly on metallic substrates; in such situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti's, with Zinsser primer Cover-Stain.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

Apply in a dry and well-ventilated area. Temperature minimum 10°C. Relative humidity max. 80%

## APLIKÁCIA A RIEDENIE: ŠTETEC

By preference, apply undiluted with flat brush.

## APLIKÁCIA A RIEDENIE: VALEC

By preference, apply undiluted with flat brush.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 015 / Pressure: 180 bars.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Possible with maximum 3% volume White Spirit.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit or Thinner 22

## POZNÁMKY

May be applied on slightly damp wood (< 20%).

## DATA SAFETY DATA

Kategória VOC:	A/d
Limit VOC:	300 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu