

Quality Paints since 1845
MATHYS[®]



FASSICRYL MATT

Water-based scratch-resistant matt lacquer

- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention
- Easy to apply with a brush and a roller



FASSICRYL MATT

POPIS PRODUKTU (DLHÝ)

Fassicryl Matt is a top-quality water-based matt indoor lacquer based on PU acrylate. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Matt is scratch-resistant and skin grease-resistant. The paint has excellent flow viscosity and good colour and gloss retention.

ODPORÚČANÉ POUŽITIE

This water-based scratch-free matt lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

ODPORÚČANÝ SYSTÉM

Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TECHNICAL_DATA

Hustota (g/cm³): 1,23 (white - wit - blanc - weiß)
Úroveň lesku: Matt
Úroveň lesku pri 60°: 5-10%
Obsah pevných látok v objeme: 37% (white - wit - blanc - weiß)

DRY_TIMES_BY_20

Na dotyk suché: 1 hour
Suchý na opätovné natieranie: 6 hours

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

67 µm (white - wit - blanc - weiß)

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

25 µm (white - wit - blanc - weiß)

TEORETICKÁ SPOTREBA

15 m²/l/coat

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.

New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.

Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

NÁVOD NA POUŽITIE

To ensure homogeneity, thoroughly stir prior to use.

PODMIENKY APLIKÁCIE

> 8°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted with brush with synthetic bristles.

APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted with a 10 mm micro fiber roller.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Clean the material with water and dispose of the residue appropriately.

POZNÁMKY

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

Scratch-resistance is achieved after 15-30 days depending on the colour.

DATA SAFETY DATA

Úroveň VOC: 40g/l
VOC readymix: 40g/l
Kategória VOC: IIA/d
Limit VOC: 130g/l
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.

Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)

Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.

38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.

Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu