

Quality Paints since 1845
MATHYS[®]



FASSICRYL MATT SPRAY

Sprayable water-based matt lacquer

- Sprayable (airless and airmix)
- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention



FASSICRYL MATT SPRAY

DESCRIZIONE

Fassicryl Matt Spray is a top-quality sprayable water-based matt indoor lacquer based on PU acrylate with excellent coverage. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Matt Spray is scratch-resistant and skin grease-resistant. The paint is slightly thixotropic, has excellent flow viscosity and good colour and gloss retention. Can be applied with a brush.

UTILIZZO CONSIGLIATO

This sprayable water-based scratch-free matt lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

SISTEMA CONSIGLIATO

Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

DATI TECNICI

Densità:	1,20 (white - wit - blanc - weiß)
Livello di lucentezza:	Opaco
Livello di lucentezza a 60°:	5-10%
Residuo secco in volume:	35% (white - wit - blanc - weiß)

TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto:	1 hour
Asciutto da rivestire:	6 hours

SPESSORE DELLA PELLICOLA UMIDA CONSIGLIATO

150-250 µm

CONSUMO TEORICO

4-6 m²/l/coat

CONSUMO PRATICO

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PREPARAZIONE DELLA SUPERFICIE

The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.

New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.

Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

ISTRUZIONI PER L'USO

To ensure homogeneity, thoroughly stir prior to use.

CONDIZIONI DI APPLICAZIONE

> 8°C, < 80% R.H.

APPLICAZIONE E DILUIZIONE: PENNELLO

This sprayable paint can also be applied with a brush. Apply undiluted with brush with synthetic bristles.

APPLICAZIONE E DILUIZIONE: SPRAY SENZ'ARIA

Nozzle: 0.009 - 0.012 / Pressure: Ca. 70 bars

The product is ready for use; do not dilute.

APPLICAZIONE E DILUIZIONE: SPRAY AD ARIA-ATOMIZZATA

Air-assist - Nozzle: 0.009 - 0.012 / Pressure: Ca. 60 bars / Air pressure: Ca.2 bars

The product is ready for use; do not dilute.

PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Clean the material with water and dispose of the residue appropriately.

NOTE

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

Scratch-resistance is achieved after 15-30 days depending on the colour.

DATI RELATIVI ALLA SICUREZZA

Livello di COV:	35g/l
Soluzione premiscelata COV:	35g/l
Categoria COV:	IIA/d
Limite di COV:	130g/l
Note riguardanti la sicurezza:	Consult Safety Data Sheet and Safety Information printed on the can.

SCADENZA

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Data del rilascio: 07/02/2025

Colori e formati di confezione disponibili: Si prega di consultare la pagina relativa al prodotto su www.rust-oleum.eu per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

Dichiarazione di non responsabilità: Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da www.rust-oleum.eu o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu