

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## FASSICRYL MATT SPRAY

# Sprayable water-based matt lacquer

- Sprayable (airless and airmix)
- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention



# FASSICRYL MATT SPRAY

## OPIS

Fassicryl Matt Spray is a top-quality sprayable water-based matt indoor lacquer based on PU acrylate with excellent coverage. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Matt Spray is scratch-resistant and skin grease-resistant. The paint is slightly thixotropic, has excellent flow viscosity and good colour and gloss retention. Can be applied with a brush.

## ZALECANE UŻYCIĘ

This sprayable water-based scratch-free matt lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

## ZALECANY SYSTEM

Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

## DANE TECHNICZNE

Gęstość:	1,20 (white - wit - blanc - weiß)
Stopień połysku:	Mat
Stopień połysku w 60:	5-10%
Zawartość substancji stałych	
objętościowo:	35% (white - wit - blanc - weiß)

## CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk:	1 hour
Do przemalowania:	6 hours

## ZALECANA GRUBOŚĆ WARSTWY NA MOKRO

150-250 µm

## ZUŻYCIĘ TEORETYCZNE

4-6 m<sup>2</sup>/l/coat

## ZUŻYCIĘ PRAKTYCZNE

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRZYGOTOWANIE POWIERZCHNI

The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.

New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.

Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

## WSKAZÓWKI DOTYCZĄCE UŻYCIA

To ensure homogeneity, thoroughly stir prior to use.

## WARUNKI APLIKACJI

> 8°C, < 80% R.H.

## APLIKACJA I ROZCIEŃCZANIE: PĘDZEL

This sprayable paint can also be applied with a brush. Apply undiluted with brush with synthetic bristles.

## APLIKACJA I ROZCIEŃCZANIE: NATRYSK BEZPOWIETRZNY

Nozzle: 0.009 - 0.012 / Pressure: Ca. 70 bars

The product is ready for use; do not dilute.

## APLIKACJA I ROZCIEŃCZANIE: NATRYSK POWIETRZNY

Air-assist - Nozzle: 0.009 - 0.012 / Pressure: Ca. 60 bars / Air pressure: Ca.2 bars

The product is ready for use; do not dilute.

## CZYSZCZENIE NARZĘDZI / ZABRUDZEŃ

Clean the material with water and dispose of the residue appropriately.

## UWAGI

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

Scratch-resistance is achieved after 15-30 days depending on the colour.

## INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO:	35g/l
Zawartość LZO w gotowej mieszaninie:	35g/l
Kategoria LZO:	IIA/d
Limity LZO:	130g/l
Uwagi dotyczące bezpieczeństwa:	Consult Safety Data Sheet and Safety Information printed on the can.

## OKRES TRWAŁOŚCI PRODUKTU

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Data wydania: 07/02/2025

**Dostępne kolory i opakowania:** Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej [www.rust-oleum.eu](http://www.rust-oleum.eu).

**Zrzeczenie się:** Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu