



Quality Paints since 1845
MATHYS[®]



FASSICRYL PRIMER

Water-based primer

- Superb adhesion
- Perfect flow viscosity
- Good coverage
- Easy to apply



FASSICRYL PRIMER

BESKRIVELSE

Fassicryl Primer is a water-based primer with excellent adhesion, for indoor and outdoor use. Based on an acrylic dispersion and PU-Alkyd emulsion. Fast-drying adhesive primer with perfect flow viscosity. Suitable as a primer for various wood types and properly cleaned paint layers with good adhesion. Can also be applied to plastic and non-ferrous metals.

ANBEFALT BRUK

Primer for application to various wood types before painting and properly cleaned old paint layers with good adhesion.

ANBEFALT SYSTEM

Priming a surface with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TEKNISKE DATA

Tetthet: 1,35 (white - wit - blanc - weiß)
Glansgrad: Matt
Tørstoffinnhold i volum: 38% (white - wit - blanc - weiß)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtør: 1 hour
Overmalbar: 6 hours

ANBEFALT VÅTFILMTHYKKE

80 µm (white - wit - blanc - weiß)

ANBEFALT TØRRFILMTHYKKE

30 µm (white - wit - blanc - weiß)

TEORETISK FORBRUK

12-14 m²/l/coat

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

The surface must be dry and free of dust and grease.

Aged wood: remove until the healthy wood is exposed.

Exposed wood: degrease (Multi Cleaner), sand and remove all dust.

Old paint layers in a poor condition: strip (NR.1 GREEN PAINT STRIPPER), degrease (Multi Cleaner), sand, remove all dust and prime.

Old paint layers in a good condition: degrease (Multi Cleaner), sand and remove all dust.

Round off sharp edges so that you can apply a good coating.

BRUKSANVISNING

The product must be firmly stirred into a homogeneous substance prior to its use. Use a suitable brush or roller to apply one or two coats.

PÅFØRINGSBETINGELSER

> 8°C, < 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply undiluted with brush with synthetic bristles.

PÅFØRING & FORTYNNING: RULLE

Apply undiluted with a 10 mm micro fiber roller.

RENGJØRING AV UTSTYR/SPILL

Clean the material with water and dispose of the residue appropriately.

MERKNADER

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

SIKKERHETSDATA

VOC nivå: 50g/l
VOC ferdigblandet: 50g/l
VOC kategori: IIA/d
VOC grense: 130g/l
Merknader angående sikkerhet: Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu