



Quality Paints since 1845
MATHYS®



FASSIFORCE®

Wood impregnation

- Strengthens the wood structure
- Improves adhesion of paint



FASSIFORCE®

POPIS PRODUKTU (DLHÝ)

This impregnating agent for wood is based on a phenolic resin and Chinese wood oil blend. Strengthens and durably protects untreated or stripped wood.

ODPORÚČANÉ POUŽITIE

Impregnation of new exterior wood that is not of first quality or bare exterior wood that is damaged in some way.

TECHNICAL DATA

Hustota (g/cm ³):	0,85 - 0,87
Úroveň lesku pri 60°:	Glossy, after saturation of the wood: ± 90%
Obsah pevných látok v hmotnosti:	± 35 %
Obsah pevných látok v objeme:	± 28 %

DRY TIMES BY 20

Na dotyk suché:	2,5 hours
Suché na manipuláciu:	3 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdnuté:	± 1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

28 µm

TEORETICKÁ SPOTREBA

± 10 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Remove old traces of paint or varnish either by scraping or thermal or chemical removal (Rapid Super). The wood must be dry sanded, degreased and made dust free, if necessary, followed by a coat of FassiForce. On some very damaged porous wood parts a second coat may be necessary.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Work in a dry and well-ventilated area. > 5°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

All types. If necessary dilute with white spirit.

APLIKÁCIA A RIEDENIE: VALEC

Not recommended.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Not recommended.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Yes, do not dilute.

ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit.

DATA SAFETY DATA

Úroveň VOC:	555 g/l
VOC readymix:	555 g/l
Kategória VOC:	A/h
Limit VOC:	750 g/l
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu