



## FASSILUX<sup>®</sup> AQUA XPE GLOSS

### High gloss topcoat for indoor and outdoor works

- Quick drying
- Low in odour and VOC
- Easy to apply
- Excellent flow and levelling characteristics
- Superior scratch resistance



# FASSILUX® AQUA XPE GLOSS

## POPIS PRODUKTU (DLOUHÝ)

A high gloss PU/Alkyd topcoat for indoor and outdoor works. Can be applied on wood and all other well prepared substrates. Especially suited for obtaining a smooth finishing.

## DOPORUČENÉ POUŽITÍ

As scratch resistant finish on properly prepared wooden or other already painted mineral substrates.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,2
Úroveň lesku:	Gloss
Obsah pevných látek v hmotnosti:	50%
Obsah pevných látek v objemu:	38%

## DRY TIMES BY 20

Dotykem suché:	3 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	1 week

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

80 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

30 µm

## TEORETICKÁ SPOTŘEBA

12 m<sup>2</sup>/l

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

- New work: the substrate needs to be clean, dry and free of fats and oils. The substrate has to be primed with Fassiprim Aqua.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.
- Block wood knots and sap streaks with Zinsser primer B-I-N.
- Interior: for stain, graffiti, tannin and other substances bleed blocking, and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus.
- Exterior: block tannin or other typical bleeding substances from redwoods etc, block graffiti, and/or for very fast recoating, use with Zinsser primer Cover-Stain.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

- 10-30 degrees C
- Relative Humidity < 80%
- Temperature of substrate at least 3 degrees C above dew point.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

If necessary dilute with maximum 5% volume water.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

If necessary dilute with maximum 5% volume water.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

- Nozzle 0.011-0.013 inch/ Pressure 120 bars
- Thinning with 3% volume water.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

- Nozzle: 1,5-2mm / Pressure 2-3 bars
- Thinning with 10-15% volume water.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Warm water

## POZNÁMKY

Conventional spraying might result in a slightly lower gloss.

## DATA SAFETY DATA

Úroveň těkavých organických látek:	14 g/l
Kategorie VOC:	A/d
Limitní hodnota VOC:	130 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 1 years from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C°

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu