



FASSILUX[®] AQUA XPE GLOSS

High gloss topcoat for indoor and outdoor works

- Quick drying
- Low in odour and VOC
- Easy to apply
- Excellent flow and levelling characteristics
- Superior scratch resistance



FASSILUX® AQUA XPE GLOSS

BESKRIVELSE

A high gloss PU/Alkyd topcoat for indoor and outdoor works. Can be applied on wood and all other well prepared substrates. Especially suited for obtaining a smooth finishing.

ANBEFALT BRUK

As scratch resistant finish on properly prepared wooden or other already painted mineral substrates.

TEKNISKE DATA

Tetthet:	1,2
Glansgrad:	Blank
Tørrstoffinnhold i vekt:	50%
Tørrstoffinnhold i volum:	38%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	3 hours
Overmalbar:	24 hours
Herdetid:	1 week

ANBEFALT VÅTFILMTYKKELSE

80 µm

ANBEFALT TØRRFILMTYKKELSE

30 µm

TEORETISK FORBRUK

12 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

- New work: the substrate needs to be clean, dry and free of fats and oils. The substrate has to be primed with Fassiprim Aqua.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.
- Block wood knots and sap streaks with Zinsser primer B-I-N.
- Interior: for stain, graffiti, tannin and other substances bleed blocking, and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus.
- Exterior: block tannin or other typical bleeding substances from redwoods etc, block graffiti's, and/or for very fast recoating, use with Zinsser primer Cover-Stain.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

- 10-30 degrees C
- Relative Humidity < 80%
- Temperature of substrate at least 3 degrees C above dew point.

PÅFØRING & FORTYNNING: PENSEL

If necessary dilute with maximum 5% volume water.

PÅFØRING & FORTYNNING: RULLE

If necessary dilute with maximum 5% volume water.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

- Nozzle 0.011-0.013 inch/ Pressure 120 bars
- Thinning with 3% volume water.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

- Nozzle: 1,5-2mm / Pressure 2-3 bars
- Thinning with 10-15% volume water.

RENGJØRING AV UTSTYR/SPILL

Warm water

MERKNADER

Conventional spraying might result in a slightly lower gloss.

SIKKERHETSDATA

VOC nivå:	14 g/l
VOC kategori:	A/d
VOC grense:	130 g/l (2010)
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 1 years from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C°

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu