



FASSILUX® AQUA XPE MATT

Waterbased matt PU/Alkyd topcoat for indoor works

- Specially designed for interior use
- Quick drying
- Low in odour and VOC
- Easy to apply
- Excellent flow and levelling characteristics



FASSILUX® AQUA XPE MATT

POPIS PRODUKTU (DLOUHÝ)

Water dilutable air-drying satin topcoat for interior paint applications, based on a polyurethane/alkyd emulsion.

DOPORUČENÉ POUŽITÍ

As scratch resistant matt finish on properly prepared wooden, or other already painted mineral substrates.

TECHNICAL DATA

Hustota (g/cm ³):	1,4
Úroveň lesku:	Matt
Úroveň lesku při 60°:	7%
Obsah pevných látek v hmotnosti:	60%
Obsah pevných látek v objemu:	43%

DRY TIMES BY 20

Dotykem suché:	3 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

80 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

34 µm

TEORETICKÁ SPOTŘEBA

Approx. 12 m²/l

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

- New work: the substrate needs to be clean, dry and free of fats and oils. The substrate has to be primed with Fassiprim Aqua.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.
- Block wood knots and sap streaks with Zinsser primer B-I-N.
- For stain, graffiti, tannin and other substances bleed blocking, and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

- 10-30 degrees C. Relative humidity < 80%.
- Temperature of the substrate at least 3 degrees C above the dew point.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Dilute, if necessary, up to maximum 5% volumewith water

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Dilute, if necessary, up to maximum 5% volume with water

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

- Nozzle: 0,011 - 0,013 inch / Pressure: 120 bars.
- Thinning 3% volume water.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

- Nozzle 1,5 - 2,0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Warm water.

POZNÁMKY

If conventional spraying is used, the gloss might be somewhat lower.

DATA SAFETY DATA

Úroveň těkavých organických látek:	30 g/l max
Kategorie VOC:	A/d
Limitní hodnota VOC:	130 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu