



FASSILUX® AQUA XPE MATT

Waterbased matt PU/Alkyd topcoat for indoor works

- Specially designed for interior use
- Quick drying
- Low in odour and VOC
- Easy to apply
- Excellent flow and levelling characteristics



FASSILUX® AQUA XPE MATT

POPIS PRODUKTU (DLHÝ)

Water dilutable air-drying satin topcoat for interior paint applications, based on a polyurethane/alkyd emulsion.

ODPORÚČANÉ POUŽITIE

As scratch resistant matt finish on properly prepared wooden, or other already painted mineral substrates.

TECHNICAL DATA

Hustota (g/cm ³):	1,4
Úroveň lesku:	Matt
Úroveň lesku pri 60°:	7%
Obsah pevných látok v hmotnosti:	60%
Obsah pevných látok v objeme:	43%

DRY TIMES BY 20

Na dotyk suché:	3 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdené:	1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

80 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

34 µm

TEORETICKÁ SPOTREBA

Approx. 12 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

- New work: the substrate needs to be clean, dry and free of fats and oils. The substrate has to be primed with Fassiprim Aqua.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.
- Block wood knots and sap streaks with Zinsser primer B-I-N.
- For stain, graffiti, tannin and other substances bleed blocking, and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

- 10-30 degrees C. Relative humidity < 80%.
- Temperature of the substrate at least 3 degrees C above the dew point.

APLIKÁCIA A RIEDENIE: ŠTETEC

Dilute, if necessary, up to maximum 5% volumewith water

APLIKÁCIA A RIEDENIE: VALEC

Dilute, if necessary, up to maximum 5% volume with water

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

- Nozzle: 0,011 - 0,013 inch / Pressure: 120 bars.
- Thinning 3% volume water.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

- Nozzle 1,5 - 2,0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Warm water.

POZNÁMKY

If conventional spraying is used, the gloss might be somewhat lower.

DATA SAFETY DATA

Úroveň VOC:	30 g/l max
Kategória VOC:	A/d
Limit VOC:	130 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu