

Quality Paints since 1845  
**MATHYS**<sup>®</sup>

## FASSILUX<sup>®</sup> AQUA XPE SATIN

# Water dilutable air-drying satin topcoat

- Can be used in- and exterior
- Quick drying
- Low in odour and VOC,
- Easy to apply
- Excellent flow and levelling characteristics



# FASSILUX® AQUA XPE SATIN

## POPIS PRODUKTU (DLHÝ)

Waterbased satin gloss PU/ Alkyd topcoat for indoor and outdoor works

## ODPORÚČANÉ POUŽITIE

As scratch resistant satin finish on properly prepared wooden, or other already painted mineral substrates.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,4
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	30 - 35%
Obsah pevných látok v hmotnosti:	57%
Obsah pevných látok v objeme:	39%

## DRY TIMES BY 20

Na dotyk suché:	3 hours
Suché na manipuláciu:	24 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdnuté:	1 week

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

80 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

30 µm

## TEORETICKÁ SPOTREBA

Approx. 12 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

- New work: the substrate needs to be clean, dry and free of fats and oils. The substrate has to be primed with Fassiprim Aqua.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.
- Block wood knots and sap streaks with Zinsser primer B-I-N.
- Interior: for stain, graffiti, tannin and other substances bleed blocking, and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus.
- Exterior: block tannin or other typical bleeding substances from redwoods etc, block graffiti, and/or for very fast recoating, use with Zinsser primer Cover-Stain.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

10-30 degrees C. Relative humidity < 80%. Temperature of the substrate at least 3 degrees C above the dew point.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Dilute, if necessary, up to maximum 5% volume with water.

## APLIKÁCIA A RIEDENIE: VALEC

Dilute, if necessary, up to maximum 5% volume with water.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

- Nozzle: 0,011 - 0,013 inch / Pressure: 120 bars.
- Thinning 3% volume water.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

- Nozzle 1.5 - 2.0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Warm water.

## POZNÁMKY

If conventional spraying is used, the gloss might be somewhat lower.

## DATA SAFETY DATA

Úroveň VOC:	12 g/l max.
Kategória VOC:	A/d
Limit VOC:	130 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATEĽNOSŤ

Minimum of 1 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu