

Quality Paints since 1845
MATHYS[®]

FASSILUX[®] AQUA XPE SATIN

Water dilutable air-drying satin topcoat

- Can be used in- and exterior
- Quick drying
- Low in odour and VOC,
- Easy to apply
- Excellent flow and levelling characteristics



FASSILUX® AQUA XPE SATIN

BESKRIVNING

Waterbased satin gloss PU/ Alkyd topcoat for indoor and outdoor works

REKOMMENDERAD ANVÄNDNING

As scratch resistant satin finish on properly prepared wooden, or other already painted mineral substrates.

TEKNISK DATA

Densitet:	1,4
Glansnivå:	Satin
Glansnivå vid 60°:	30 - 35%
Torrsubstansvikt:	57%
Torrsubstansvolym:	39%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	3 hours
Hanteringstorr:	24 hours
Övermålningsbar:	24 hours
Fullt härdad:	1 week

REKOMMENDERAD VÅTFILMSTJOCKLEK

80 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

30 µm

TEORETISK FÖRBRUKNING

Approx. 12 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

- New work: the substrate needs to be clean, dry and free of fats and oils. The substrate has to be primed with Fassiprim Aqua.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.
- Block wood knots and sap streaks with Zinsser primer B-I-N.
- Interior: for stain, graffiti, tannin and other substances bleed blocking, and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus.
- Exterior: block tannin or other typical bleeding substances from redwoods etc, block graffiti, and/or for very fast recoating, use with Zinsser primer Cover-Stain.
-

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

10-30 degrees C. Relative humidity < 80%. Temperature of the substrate at least 3 degrees C above the dew point.

APPLICERING OCH SPÄDNING: PENSEL

Dilute, if necessary, up to maximum 5% volume with water.

APPLICERING OCH SPÄDNING: ROLLER

Dilute, if necessary, up to maximum 5% volume with water.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

- Nozzle: 0,011 - 0,013 inch / Pressure: 120 bars.
- Thinning 3% volume water.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

- Nozzle 1.5 - 2.0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

RENGÖRING AV UTRUSTNING/SPILL

Warm water.

ANMÄRKNINGAR

If conventional spraying is used, the gloss might be somewhat lower.

SÄKERHETSDATA

VOC-nivå:	12 g/l max.
VOC-kategori:	A/d
VOC-gräns:	130 g/l (2010)
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 1 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu