

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## FASSILUX<sup>®</sup> GLOSS

### Solvent based high gloss enamel

- Simple and fast application
- Excellent flow
- Excellent scratch and wear resistance
- Good outdoor durability, weatherproof
- Quick drying

# FASSILUX® GLOSS

## POPIS PRODUKTU (DLOUHÝ)

Solvent based high gloss enamel based on alkyd resins.

## DOPORUČENÉ POUŽITÍ

Topcoat for interior and exterior woodwork.

## DOPORUČENÝ SYSTÉM

### TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,17 - 1,20
Úroveň lesku:	Gloss
Obsah pevných látek v hmotnosti:	77 - 79 %
Obsah pevných látek v objemu:	70 - 72 %

### DRY TIMES BY 20

Dotykem suché:	3 hours
Suché na manipulaci:	4 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	1 week

### DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

50 µm

### DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

35 µm

### TEORETICKÁ SPOTŘEBA

20 m<sup>2</sup>/l per coat

### PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### PŘÍPRAVA POVRCHU

For top quality work, apply two coats of Fassiprim, sanding between each coat carefully. In some cases, the 2 coats of Fassiprim can be replaced by 1 thick coat of Fassicoat. For exterior works, it is advisable to apply an impregnating coat of FassiForce on bare or stripped wood, or on low grade wood. Do not use Fassicoat on metallic substrate; in this situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti, with Zinsser primer Cover-Stain.

### NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

### PODMÍNKY POUŽITÍ

Apply in a dry and well-ventilated area. Temperature minimum 10°C. Relative humidity maximum 80%.

### APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Do not dilute

### APLIKACE A ŘEDĚNÍ: VÁLEČEK

Do not dilute

### APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 09 - 013 / Pressure: 180 bars. Do not dilute.

### APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Do not dilute

### ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit or Thinner 22.

### POZNÁMKY

Apply Fassilux in thin layers.

### DATA SAFETY DATA

Úroveň těkavých organických látek:	300
Kategorie VOC:	A/d
Limitní hodnota VOC:	300 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

### DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu