



FASSILUX[®] SATIN PU

Solvent based satin gloss enamel

- Highly abrasion and scratch resistant
- Based on alkyd urethane resins
- High gain
- Even gloss finish
- Quick drying

FASSILUX® SATIN PU

POPIS PRODUKTU (DLHÝ)

Fassilux Satin PU is a satin gloss enamel with an extra high resistance to abrasion and scratches. This enamel based on alkyd urethane resins is of an exceptional quality and offers a very high covering capacity. Fassilux Satin PU can be applied on wood, metal and all well prepared non alkaline substrates.

ODPORÚČANÉ POUŽITIE

Topcoat for interior and exterior works.

TECHNICAL DATA

Hustota (g/cm ³):	1,34 - 1,37
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	+ /- 20%
Obsah pevných látok v hmotnosti:	75 - 77 %
Obsah pevných látok v objeme:	59 - 62 %

DRY TIMES BY 20

Na dotyk suché:	4 hours
Suché na manipuláciu:	4-5 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdnuté:	± 1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

65 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

40 µm

TEORETICKÁ SPOTREBA

15 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

Priming coat: for wood Fassiprim, for metal use a tintable Rust-Oleum anticorrosion primer. Apply one priming coat and 1 layer of Fassilux Satin PU. For top quality painting work, apply one priming coat and 2 layers of Fassilux Satin PU. Sand between each layer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti's, with Zinsser primer Cover-Stain.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

- Apply in a dry and well-ventilated area.
- Minimum temperature: 10°C. Maximum relative humidity: 80%.

APLIKÁCIA A RIEDENIE: ŠTETEC

Do not dilute

APLIKÁCIA A RIEDENIE: VALEC

Do not dilute

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

- Nozzle: 013 - 015 / Pressure: 180 bars.
- Do not dilute.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Do not dilute

ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit or Thinner 22

DATA SAFETY DATA

Kategória VOC:	A/d
Limit VOC:	300 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu