



## **FASSILUX® SATIN**

### **First quality satin gloss**

- Simple and fast application
- Excellent flow
- Excellent scratch and wear resistance
- Good outdoor durability, weatherproof
- Quick drying

# FASSILUX® SATIN

## POPIS PRODUKTU (DLHÝ)

First quality satin gloss alkyd enamel, for interior and exterior application

## ODPORÚČANÉ POUŽITIE

Topcoat for interior and exterior woodwork.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,34 - 1,37
Úroveň lesku:	Satin
Úroveň lesku pri 60°:	+/- 30%
Obsah pevných látok v hmotnosti:	70 - 73% (wit)
Obsah pevných látok v objeme:	53 - 56 % (weiss)

## DRY TIMES BY 20

Na dotyk suché:	4 - 5 hours
Suché na manipuláciu:	5 - 6 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdené:	± 1 week

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

55 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

30 µm

## TEORETICKÁ SPOTREBA

18 m<sup>2</sup>/l

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

Priming coat: Fassiprim. For top quality painting work, apply two coats of Fassiprim, sanding between each coat carefully. For exterior works, it is advisable to apply an impregnating coat of FassiForce on bare or stripped wood, or on low grade wood. Do not use Fassicoat on metallic substrates; in this situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti, with Zinsser primer Cover-Stain.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

- Apply in a dry and well-ventilated area.
- Minimum temperature: 10°C. Maximum relative humidity: 80%

## APLIKÁCIA A RIEDENIE: ŠTETEC

Do not dilute

## APLIKÁCIA A RIEDENIE: VALEC

Do not dilute

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

- Nozzle: 013 - 015 / Pressure: 180 bars.
- Do not dilute.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Do not dilute

## ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit or Thinner 22

## POZNÁMKY

Do not use Fassilux Satin on Noxyde for outside works. In these cases, use either Fassilux or Pegacryl Satin.

## DATA SAFETY DATA

Kategória VOC:	A/d
Limit VOC:	400 g/l (2007) / 300 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu