

Quality Paints since 1845
MATHYS[®]



FASSILUX[®] GLOSS

Solvent based high gloss enamel

- Simple and fast application
- Excellent flow
- Excellent scratch and wear resistance
- Good outdoor durability, weatherproof
- Quick drying

FASSILUX® GLOSS

POPIS PRODUKTU (DLHÝ)

Solvent based high gloss enamel based on alkyd resins.

ODPORÚČANÉ POUŽITIE

Topcoat for interior and exterior woodwork.

ODPORÚČANÝ SYSTÉM

TECHNICAL DATA

Hustota (g/cm ³):	1,17 - 1,20
Úroveň lesku:	Gloss
Obsah pevných látok v hmotnosti:	77 - 79 %
Obsah pevných látok v objeme:	70 - 72 %

DRY TIMES BY 20

Na dotyk suché:	3 hours
Suché na manipuláciu:	4 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdnuté:	1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

50 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

35 µm

TEORETICKÁ SPOTREBA

20 m²/l per coat

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

For top quality work, apply two coats of Fassiprim, sanding between each coat carefully. In some cases, the 2 coats of Fassiprim can be replaced by 1 thick coat of Fassicoat. For exterior works, it is advisable to apply an impregnating coat of FassiForce on bare or stripped wood, or on low grade wood. Do not use Fassicoat on metallic substrate; in this situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti, with Zinsser primer Cover-Stain.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Apply in a dry and well-ventilated area. Temperature minimum 10°C. Relative humidity maximum 80%.

APLIKÁCIA A RIEDENIE: ŠTETEC

Do not dilute

APLIKÁCIA A RIEDENIE: VALEC

Do not dilute

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 09 - 013 / Pressure: 180 bars. Do not dilute.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Do not dilute

ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit or Thinner 22.

POZNÁMKY

Apply Fassilux in thin layers.

DATA SAFETY DATA

Úroveň VOC:	300
Kategória VOC:	A/d
Limit VOC:	300 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu