



Quality Paints since 1845
MATHYS®



FASSIPRIM AQUA XPE

Waterbased primer

- Water based, matt acrylic
- Easy to apply
- Quick drying, quick to sand
- Good coverage
- Excellent adhesion and flow



FASSIPRIM AQUA XPE

POPIS PRODUKTU (DLOUHÝ)

Waterbased, moisture regulating primer for long-lasting indoor and outdoor timberwork.

DOPORUČENÉ POUŽITÍ

Primer for different types of wood and well cleaned, well adhering old coatings.

TECHNICAL DATA

Hustota (g/cm ³):	± 1,3
Úroveň lesku:	Matt
Obsah pevných látek v hmotnosti:	± 53 %
Obsah pevných látek v objemu:	± 39 %

DRY TIMES BY 20

Dotykem suché:	1 hour
Suchý nátěr:	3 hours
Plně vytvrzené:	1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

35 µm

TEORETICKÁ SPOTŘEBA

± 10 m²/l

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

- New work: substrate has to be clean, dry and free of fats. Deteriorated wood has to be removed to the sound wood. For very porous substrates like fir and pine it is recommended to apply a second primer coat.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

10-30 degrees C. Relative humidity < 80%. Temperature of the substrate at least 3 degrees C above the dewpoint.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Dilute, if necessary, up to maximum 5% volume with water.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Dilute, if necessary, up to maximum 5% volume with water.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

- Nozzle: 0.013 inch / Pressure: 120 - 150 bars.
- Thinning 3% volume water.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

- Nozzle 1,5 - 2,0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Warm water.

DATA SAFETY DATA

Úroveň těkavých organických látek:	17 g/l max.
Kategorie VOC:	A/g
Limitní hodnota VOC:	30 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu