



## FASSIPRIM AQUA XPE

### Waterbased primer

- Water based, matt acrylic
- Easy to apply
- Quick drying, quick to sand
- Good coverage
- Excellent adhesion and flow



# FASSIPRIM AQUA XPE

## BESKRIVELSE

Waterbased, moisture regulating primer for long-lasting indoor and outdoor timberwork.

## ANBEFALT BRUK

Primer for different types of wood and well cleaned, well adhering old coatings.

## TEKNISKE DATA

Tetthet:	± 1,3
Glansgrad:	Matt
Tørrestoffinnhold i vekt:	± 53 %
Tørrestoffinnhold i volum:	± 39 %

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 hour
Overmalbar:	3 hours
Herdetid:	1 week

## ANBEFALT VÅTFILMTYKKELSE

100 µm

## ANBEFALT TØRRFILMTYKKELSE

35 µm

## TEORETISK FORBRUK

± 10 m<sup>2</sup>/l

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

- New work: substrate has to be clean, dry and free of fats. Deteriorated wood has to be removed to the sound wood. For very porous substrates like fir and pine it is recommended to apply a second primer coat.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PÅFØRINGSBETINGELSER

10-30 degrees C. Relative humidity < 80%. Temperature of the substrate at least 3 degrees C above the dewpoint.

## PÅFØRING & FORTYNNING: PENSEL

Dilute, if necessary, up to maximum 5% volume with water.

## PÅFØRING & FORTYNNING: RULLE

Dilute, if necessary, up to maximum 5% volume with water.

## PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

- Nozzle: 0.013 inch / Pressure: 120 - 150 bars.
- Thinning 3% volume water.

## PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

- Nozzle 1,5 - 2,0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

## RENGJØRING AV UTSTYR/SPILL

Warm water.

## SIKKERHETSDATA

VOC nivå:	17 g/l max.
VOC kategori:	A/g
VOC grense:	30 g/l (2010)
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu