



FASSIPRIM AQUA XPE

Waterbased primer

- Water based, matt acrylic
- Easy to apply
- Quick drying, quick to sand
- Good coverage
- Excellent adhesion and flow



FASSIPRIM AQUA XPE

POPIS PRODUKTU (DLHÝ)

Waterbased, moisture regulating primer for long- lasting indoor and outdoor timberwork.

ODPORÚČANÉ POUŽITIE

Primer for different types of wood and well cleaned, well adhering old coatings.

TECHNICAL DATA

Hustota (g/cm ³):	± 1,3
Úroveň lesku:	Matt
Obsah pevných látok v hmotnosti:	± 53 %
Obsah pevných látok v objeme:	± 39 %

DRY TIMES BY 20

Na dotyk suché:	1 hour
Suchý na opätovné natieranie:	3 hours
Úplne vytvrdené:	1 week

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

35 µm

TEORETICKÁ SPOTREBA

± 10 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

- New work: substrate has to be clean, dry and free of fats. Deteriorated wood has to be removed to the sound wood. For very porous substrates like fir and pine it is recommended to apply a second primer coat.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

10-30 degrees C. Relative humidity < 80%. Temperature of the substrate at least 3 degrees C above the dewpoint.

APLIKÁCIA A RIEDENIE: ŠTETEC

Dilute, if necessary, up to maximum 5% volume with water.

APLIKÁCIA A RIEDENIE: VALEC

Dilute, if necessary, up to maximum 5% volume with water.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

- Nozzle: 0.013 inch / Pressure: 120 - 150 bars.
- Thinning 3% volume water.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

- Nozzle 1,5 - 2,0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Warm water.

DATA SAFETY DATA

Úroveň VOC:	17 g/l max.
Kategória VOC:	A/g
Limit VOC:	30 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu