



Quality Paints since 1845
MATHYS®



FASSIPRIM AQUA XPE

Waterbased primer

- Water based, matt acrylic
- Easy to apply
- Quick drying, quick to sand
- Good coverage
- Excellent adhesion and flow



FASSIPRIM AQUA XPE

BESKRIVNING

Waterbased, moisture regulating primer for long-lasting indoor and outdoor timberwork.

REKOMMENDERAD ANVÄNDNING

Primer for different types of wood and well cleaned, well adhering old coatings.

TEKNISK DATA

Densitet:	± 1,3
Glansnivå:	Matt
Torrsubstansvikt:	± 53 %
Torrsubstansvolym:	± 39 %

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour
Övermålningsbar:	3 hours
Fullt härdad:	1 week

REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

35 µm

TEORETISK FÖRBRUKNING

± 10 m²/l

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

- New work: substrate has to be clean, dry and free of fats. Deteriorated wood has to be removed to the sound wood. For very porous substrates like fir and pine it is recommended to apply a second primer coat.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

10-30 degrees C. Relative humidity < 80%. Temperature of the substrate at least 3 degrees C above the dewpoint.

APPLICERING OCH SPÄDNING: PENSEL

Dilute, if necessary, up to maximum 5% volume with water.

APPLICERING OCH SPÄDNING: ROLLER

Dilute, if necessary, up to maximum 5% volume with water.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

- Nozzle: 0.013 inch / Pressure: 120 - 150 bars.
- Thinning 3% volume water.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

- Nozzle 1,5 - 2,0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

RENGÖRING AV UTRUSTNING/SPILL

Warm water.

SÄKERHETSDATA

VOC-nivå:	17 g/l max.
VOC-kategori:	A/g
VOC-gräns:	30 g/l (2010)
Anmärkingar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu