

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## FASSITEK<sup>®</sup> AQUA OPAQUE

### Wood Stain

- Can be used as a primer or as a finishing layer
- Enhances the wood structure and grain
- Good outdoor durability, weatherproof
- Microporous – allows wood to breathe
- Flexible system



# FASSITEK® AQUA OPAQUE

## BESKRIVELSE

Water based durable and low sheen opaque exterior wood finish. Fassitek® Aqua Opaque offers a durable protection whilst the wood structure stays visible.

## ANBEFALT BRUK

Tintable semi-gloss waterborne opaque wood stain for the protection and decoration of wood. Fassitek Aqua Opaque is also suitable for the decoration of brick and concrete. Can also be used on cladding, fascias, panelling, sheds, gates, fences, garden furniture, windows and doors.

## TEKNISKE DATA

Tetthet:	1,10-1,25
Glansgrad:	Satinert
Tørrestoffinnhold i volum:	42-47 %

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Overmalbar:	Minimum 2 hours
Herdetid:	4 hours

## ANBEFALT VÅTFILMTYKKELSE

80-100 µm

## ANBEFALT TØRRFILMTYKKELSE

35-45 µm

## TEORETISK FORBRUK

- Sawn : 4-8 m<sup>2</sup>/litre.
- Planed: 8-12 m<sup>2</sup>/litre.

## PRAKTISK FORBRUK

Practical coverage dependson many fac-tors such as porosity and roughness of the substrate and material losses during appli-cation.

## KLARGJØRING AV OVERFLATE

It is recommended that all non-durable timber for outer use should be treated with a preserva-tive. Wood should be un-weathered, bare, dry, free of mould, dirt, bark, paint, varnish or polish.Rough-sawn wood should be treated. Moisture content should be less than 21% at the time of treatment. Avoid application of Fassitek Aqua Opaque on (horizontal) surfaces containing moisture. Remove fungi with a suitable cleaning agent. Wood should be degreased, then care-fully sanded and dedusted.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.Apply by brush or roller, being careful to avoid overbrushing/rolling and to achieve the recom-mended coverage. External window joinery: It is important to ensure that only top-quality joinery is used and that the timber has been adequately preserved.In the context of maintenance work: if you use putty based on linseed oil, you should first apply a primer with the same base. Let it dry for at least 24 hours. If you use putty based on acrylic, you can apply the Fassitek Aqua Opaque immediately.

## PÅFØRINGSBETINGELSER

> 10°C,<30°C en < 80% r.h.The temperature of the substrate should be at least 3°C above the dew point. Always apply the wood stain under conditions facilitating drying times, if possible when no wind is present. It may not rain during the first three hours of drying time

## PÅFØRING & FORTYNNING: PENSEL

Brush for waterborne lacquers.

## PÅFØRING & FORTYNNING: RULLE

Microfiber roller 5 or 10 mm, depending the desired finish

## RENGJØRING AV UTSTYR/SPILL

Water

## MERKNADER

Fassitek Aqua Opaque is not suitable for surfaces subject to heavy continuous wear, eg. from foot traffic.It is suitable for greenhouses and animal quarters. Withhold plants and animals out of this area during drying time. Apply a third coat on horizontal surfaces such as windowsills. Fassitek Aqua Opaque is compatible with protection treatments without water repelling additives.If you should use the wood stain on coniferous wood, we recommend to insulate the knots prior to application, especially when using bright colours. A discoloration as a result of resin bleeding may be possible.

## SIKKERHETSDATA

VOC nivå:	130 g/l
VOC kategori:	A/e
VOC grense:	max. 130 g/l (2010)
Merknader angående sikkerhet:	Consult Material Safety Data Sheet and Safety Information printed on the can

## HOLDBARHET

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas,not in direct sunlight at temperatures between 5°and 35°C.

Utstedt dato: 07/02/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillter Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu