

Quality Paints since 1845
MATHYS[®]



FASSITEK[®]

Wood stain

- Transparent and light-stable
- Penetrates for deep protection
- Non film-forming
- Enhances the wood structure
- Microporous, allows the wood to breathe



POPIS PRODUKTU (DLHÝ)

Fassitek is a solvent based stain with a base of special alkyd resins. These stains are very effective in impregnating wood and protecting many types of wood from weathering and UV rays

ODPORÚČANÉ POUŽITIE

Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance - micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

TECHNICAL_DATA

Hustota (g/cm ³):	0,87 - 0,90
Úroveň lesku:	Semi-Matt
Obsah pevných látok v hmotnosti:	± 38 %
Obsah pevných látok v objeme:	± 30 %

DRY_TIMES_BY_20

Na dotyk suché:	3 hours (15 m ² /l)
Suché na manipuláciu:	3 hours (15 m ² /l)
Suchý na opätovné natieranie:	24 hours

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 micron (cons.: 10 m²/l)

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

30 micron (cons.: 10 m²/l)

TEORETICKÁ SPOTREBA

10 - 15 m²/l

PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PRÍPRAVA POVRCHU

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit, Afzelia with ammonia water. Old stripped paint: rub down up to the bare not impregnated wood fibre and make dust free. Maintenance on Fassitek: clean substrate with white spirit and apply 2 or 3 thin coats.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

By preference, apply undiluted.

APLIKÁCIA A RIEDENIE: VALEC

By preference, apply undiluted.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

By preference, apply undiluted.

ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit or Thinner 22

POZNÁMKY

Incorrect use of Fassitek means that it can still be fully or partly removed with Thinner 22 within the first few days after application

DATA_SAFETY_DATA

Úroveň VOC:	565 g/l max
Kategória VOC:	A/f
Limit VOC:	700 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATELNOSŤ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu