

Quality Paints since 1845
MATHYS[®]



FASSITEK[®] THIXO

Slight thixotropic solvent based wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film-forming
- Enhances the wood structure

FASSITEK® THIXO

POPIS PRODUKTU (DLOUHÝ)

Fassitek® Thixo is an easy to apply thixotropic stain. This Fassitek® version has all the protective and cosmetic qualities of the classic Fassitek®, but is slightly thicker in texture. This means that a thicker coating of the product can be applied and makes it more convenient to use, especially for overhead work.

DOPORUČENÉ POUŽITÍ

Protective and decorative impregnation of interior and exterior woodwork.
Remark: colourless Fassitek is only suitable for internal use

TECHNICAL DATA

Hustota (g/cm ³):	0,86-0,89
Úroveň lesku:	Semi-Matt
Obsah pevných látek v hmotnosti:	37-40 %
Obsah pevných látek v objemu:	30-33 %

DRY TIMES BY 20

Dotykem suché:	3 hours
Suché na manipulaci:	3 hours
Suchý nátěr:	24 hours

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 microns

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

32 microns

TEORETICKÁ SPOTŘEBA

10 m²/l

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

PŘÍPRAVA POVRCHU

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit; Afzelia with ammonia water.
Old stripped paint: rub down to the bare not impregnated wood fibre and make dust free.
Maintenance on Fassitek Thixo: clean substrate with white spirit and apply 2 or 3 thin coats.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

By preference, apply undiluted.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

By preference, apply undiluted.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

By preference, apply undiluted. Nozzle: 0.009 - 0.013 / Pressure: 150 bar

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

By preference, apply undiluted.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White Spirit or Thinner 22

POZNÁMKY

Incorrect use of Fassitek Thixo means that it can still be fully or partially removed with Thinner 22 within the first few days after application.

DATA SAFETY DATA

Úroveň těkavých organických látek:	550 g/l
VOC readymix:	550 g/l
Kategorie VOC:	A/f
Limitní hodnota VOC:	700 g/l
Poznámky k bezpečnosti:	Consult Material Safety Data Sheet and safety information printed on the can

DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight, at temperatures between 5 and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu