



## FASSITHANE GLOSS

# Wood Varnish

- Quick drying
- Does not yellow
- Scratch and wear resistant
- No tendency to wrinkle when applying thick layers
- Satin and Gloss versions: use indoors and outdoors



# FASSITHANE GLOSS

## POPIS PRODUKTU (DLHÝ)

First quality polyurethane wood varnish for interior and exterior use

## ODPORÚČANÉ POUŽITIE

Hard, durable finishing varnish on wood for interior and exterior use.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	0,90 - 0,92
Úroveň lesku:	Gloss
Úroveň lesku pri 60°:	>90%
Obsah pevných látok v hmotnosti:	49,5 – 51,5 %
Obsah pevných látok v objeme:	42 - 44 %

## DRY TIMES BY 20

Na dotyk suché:	1½ hours
Suché na manipuláciu:	2 hours
Suchý na opätovné natieranie:	6 hours
Úplne vytvrdnuté:	7 days

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

65 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

30 µm

## TEORETICKÁ SPOTREBA

± 15 m<sup>2</sup>/l per coat

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

The substrate must be smooth and completely dry and clean. New wood: rub down and make dustfree (use a cloth damped in white spirit). Degrease resinous or exotic wood with thinner. Remove old varnish layers with a paint stripper (Rapid Super). After this rub down lightly and clean with white spirit. Old varnish layers with good adhesion: rub down lightly and clean. Restore discoloured parts with Fassitek and rub down.

### New wood:

- Impregnate with FassiForce or Fassitek if it is necessary to colour the wood.
- If colouring is not necessary, first apply a thinned coat Fassithane Gloss.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

Apply in a dry and well-ventilated area. Temperature of air, substrate and coating material between 10 and 35°C and relative humidity below 80%. The substrate temperature must be at least 3°C above dew point.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Do not dilute.

## APLIKÁCIA A RIEDENIE: VALEC

Do not dilute.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Do not dilute.

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Do not dilute.

## ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit or Thinner 22.

## POZNÁMKY

In case of exterior applications use at least 3 coats Fassithane Gloss. In case the recoat time between successive coats is longer than 24 hours, it is necessary to clean the surface with a cloth soaked in white spirit in order to achieve a good adhesion.

## DATA SAFETY DATA

Úroveň VOC:	400 g/l max.
Kategória VOC:	A/e
Limit VOC:	400 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu