



FASSITHANE MATT

Matt Wood Varnish

- Quick drying
- Does not yellow
- Scratch and wear resistant
- No tendency to wrinkle when applying thick layers
- Use indoors

FASSITHANE MATT

POPIS PRODUKTU (DLOUHÝ)

First quality polyurethane wood varnish for interior use.

DOPORUČENÉ POUŽITÍ

Hard, durable finishing varnish on wood for interior use.

TECHNICAL DATA

Hustota (g/cm ³):	0,93 - 0,95
Úroveň lesku:	Matt
Obsah pevných látek v hmotnosti:	53 - 55 %
Obsah pevných látek v objemu:	44 - 46 %

DRY TIMES BY 20

Dotykem suché:	1½ hour
Suché na manipulaci:	2 hours
Suchý nátěr:	6 hours
Plně vytvrzené:	7 days

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

65 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

35 µm

TEORETICKÁ SPOTŘEBA

± 15 m²/l per coat

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

The substrate must be smooth and completely dry and clean. New wood: rub down and make dustfree (use a cloth dampened in white spirit). Degrease resinous or exotic wood with thinner. Remove old varnish layers with a paint stripper (Rapid Super). After this rub down lightly and clean with white spirit. Old varnish layers with good adhesion: rub down lightly and clean. Restore discoloured parts with Fassitek and rub down.

New wood:

- Impregnate with FassiForce or Fassitek if it is necessary to colour the wood.
- If colouring is not necessary, first apply a thinned coat Fassithane Matt.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Apply in a dry and well-ventilated area. Temperature of air, substrate and coating material between 10 and 35°C and relative humidity below 80%. The substrate temperature must be at least 3°C above dew point.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Do not dilute.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

If necessary dilute with maximum 10% volume white spirit or Thinner 22.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Do not dilute.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Do not dilute.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit or Thinner 22

POZNÁMKY

In case the recoat time between successive coats is longer than 24 hours, it is necessary to clean the surface with a cloth soaked in white spirit in order to achieve a good adhesion.

DATA SAFETY DATA

Úroveň těkavých organických látek:	400 g/l m
Kategorie VOC:	A/e
Limitní hodnota VOC:	400 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu