

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



**FIXONAL**

## **Colourless fixating agent**

- Fixing and reinforcing
- Alkali resistant
- Quick drying
- Flexible

[WWW.MATHYSPAINTS.EU](http://WWW.MATHYSPAINTS.EU)

# FIXONAL

## POPIS PRODUKTU (DLOUHÝ)

Fixating varnish based on acrylic polymers to strengthen all porous or chalking substrates.

## DOPORUČENÉ POUŽITÍ

Fixation of chalking substrates. Reinforces the adhesion of the new coat on the old paint and makes more flexible.

## TECHNICAL\_DATA

Hustota (g/cm <sup>3</sup> ):	0,81 - 0,83
Úroveň lesku při 60°:	> 90%
Obsah pevných látek v hmotnosti:	19%
Obsah pevných látek v objemu:	15%

## DRY\_TIMES\_BY\_20

Dotykem suché:	± 45 minutes
Suché na manipulaci:	± 1 hour
Suchý nátěr:	± 2 - 4 hours
Plně vytvrzené:	± 1 day

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

15 µm

## TEORETICKÁ SPOTŘEBA

± 10 - 15 m<sup>2</sup>/l, according to the porosity of the substrate.

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

The surfaces to be treated must be dry, clean and adhering. Chalking substrates must be rubbed down with a hard brush and dusted off. Rub down glossy coats. Degrease if necessary. After drying, apply the topcoat as quickly as possible.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Work in a dry and well-ventilated area. > 5°C, < 80% R.H.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

By preference, do not dilute.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

By preference, do not dilute

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Not recommended

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not recommended

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit

## POZNÁMKY

Fixonal does not improve the adhesion of old paint coats on the substrate.

## DATA\_SAFETY\_DATA

Úroveň těkavých organických látek:	700 g/l max.
Kategorie VOC:	A/h
Limitní hodnota VOC:	750 g/l (2007) / 750 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu