



# **FIXONAL**

# **Colourless fixating agent**

- · Fixing and reinforcing
- Alkali resistant
- · Quick drying
- Flexible

## FIXONAL

#### DESCRIPTION

Fixating varnish based on acrylic polymers to strengthen all porous or chalking substrates.

#### **RECOMMENDED USE**

Fixation of chalking substrates. Reinforces the adhesion of the new coat on the old paint and makes more flexible.

#### **TECHNICAL DATA**

Density (g/cm³): 0,81 - 0,83
Gloss level at 60°: >90%
Solids Content in weight: 19%
Solids content in volume: 15%

#### DRY TIMES BY 20° C/RH 50%

 $\begin{array}{lll} \mbox{Touch dry:} & \pm 45 \mbox{ minutes} \\ \mbox{Dry to handle:} & \pm 1 \mbox{ hour} \\ \mbox{Dry to recoat:} & \pm 2 - 4 \mbox{ hours} \\ \mbox{Fully cured:} & \pm 1 \mbox{ day} \\ \end{array}$ 

#### RECOMMENDED WET FILM THICKNESS

100 µm

#### RECOMMENDED DRY FILM THICKNESS

15 µm

#### THEORETICAL CONSUMPTION

 $\pm$  10 - 15 m<sup>2</sup>/l, according to the porosity of the substrate.

#### PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

#### SURFACE PREPARATION

The surfaces to be treated must be dry, clean and adhering. Chalking substrates must be rubbed down with a hard brush and dusted off. Rub down glossy coats. Degrease if necessary. After drying, apply the topcoat as quickly as possible.

#### **DIRECTIONS FOR USE**

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

#### **APPLICATION CONDITIONS**

Work in a dry and well-ventilated area. > 5 °C, < 80% R.H.

#### **APPLICATION & THINNING: BRUSH**

By preference, do not dilute.

#### **APPLICATION & THINNING: ROLLER**

By preference, do not dilute

#### **APPLICATION & THINNING: AIRLESS SPRAY**

Not recommended

#### **APPLICATION & THINNING: AIR-ATOMISED SPRAY**

Not recommended

### CLEANING OF EQUIPMENT / SPILLS

White spirit

#### REMARKS

Fixonal does not improve the adhesion of old paint coats on the substrate.

#### **SAFETY DATA**

VOC level: 700 g/l max.

VOC category: A/h

VOC limit: 750 g/l (2007) / 750 g/l (2010)

Remarks regarding safety: Consult Safety Data Sheet and Safety Information

printed on the can.

#### SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

**Date issued:** 12/06/2023

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T : +31 (0) 165 593 636 F : +31 (0) 165 593 600 info@rust-oleum.eu Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@nst-leum et

Rust-Oleum France S.A.S. 38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-oleum.eu