

Quality Paints since 1845
MATHYS[®]



FIXONAL

Colourless fixating agent

- Fixing and reinforcing
- Alkali resistant
- Quick drying
- Flexible

WWW.MATHYSPAINTS.EU

FIXONAL

BESKRIVELSE

Fixating varnish based on acrylic polymers to strengthen all porous or chalking substrates.

ANBEFALT BRUK

Fixation of chalking substrates. Reinforces the adhesion of the new coat on the old paint and makes more flexible.

TEKNISKE DATA

Tetthet:	0,81 - 0,83
Glansgrad ved 60°:	> 90%
Tørrestoffinnhold i vekt:	19%
Tørrestoffinnhold i volum:	15%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtør:	± 45 minutes
Håndterbar:	± 1 hour
Overmalbar:	± 2 - 4 hours
Herdetid:	± 1 day

ANBEFALT VÅTFILMTYKKELSE

100 µm

ANBEFALT TØRRFILMTYKKELSE

15 µm

TEORETISK FORBRUK

± 10 - 15 m²/l, according to the porosity of the substrate.

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

The surfaces to be treated must be dry, clean and adhering. Chalking substrates must be rubbed down with a hard brush and dusted off. Rub down glossy coats. Degrease if necessary. After drying, apply the topcoat as quickly as possible.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Work in a dry and well-ventilated area. > 5°C, < 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

By preference, do not dilute.

PÅFØRING & FORTYNNING: RULLE

By preference, do not dilute

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Not recommended

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Not recommended

RENGJØRING AV UTSTYR/SPILL

White spirit

MERKNADER

Fixonal does not improve the adhesion of old paint coats on the substrate.

SIKKERHETSDATA

VOC nivå:	700 g/l max.
VOC kategori:	A/h
VOC grense:	750 g/l (2007) / 750 g/l (2010)
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu