

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



**FIXONAL**

## **Colourless fixating agent**

- Fixing and reinforcing
- Alkali resistant
- Quick drying
- Flexible

[WWW.MATHYSPAINTS.EU](http://WWW.MATHYSPAINTS.EU)

# FIXONAL

## BESKRIVNING

Fixating varnish based on acrylic polymers to strengthen all porous or chalking substrates.

## REKOMMENDERAD ANVÄNDNING

Fixation of chalking substrates. Reinforces the adhesion of the new coat on the old paint and makes more flexible.

## TEKNISK DATA

Densitet:	0,81 - 0,83
Glansnivå vid 60°:	> 90%
Torrsubstansvikt:	19%
Torrsubstansvolym:	15%

## TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	± 45 minutes
Hanteringstorr:	± 1 hour
Övermålningsbar:	± 2 - 4 hours
Fullt härdad:	± 1 day

## REKOMMENDERAD VÅTFILMSTJOCKLEK

100 µm

## REKOMMENDERAD TORRFILMSTJOCKLEK

15 µm

## TEORETISK FÖRBRUKNING

± 10 - 15 m<sup>2</sup>/l, according to the porosity of the substrate.

## PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## YTFÖRBEREDELSE

The surfaces to be treated must be dry, clean and adhering. Chalking substrates must be rubbed down with a hard brush and dusted off. Rub down glossy coats. Degrease if necessary. After drying, apply the topcoat as quickly as possible.

## BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICERINGSFÖRHÅLLANDEN

Work in a dry and well-ventilated area. > 5°C, < 80% R.H.

## APPLICERING OCH SPÄDNING: PENSEL

By preference, do not dilute.

## APPLICERING OCH SPÄDNING: ROLLER

By preference, do not dilute

## APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Not recommended

## APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Not recommended

## RENGÖRING AV UTRUSTNING/SPILL

White spirit

## ANMÄRKNINGAR

Fixonal does not improve the adhesion of old paint coats on the substrate.

## SÄKERHETSDATA

VOC-nivå:	700 g/l max.
VOC-kategori:	A/h
VOC-gräns:	750 g/l (2007) / 750 g/l (2010)
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

## HÅLLBARHET

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

Utgivet den: 07/02/2025

**Tillgängliga färger och förpackningsstorlekar:** Se respektive produktsida på [www.rust-oleum.eu](http://www.rust-oleum.eu) för en översikt över tillgängliga färger och förpackningsstorlekar.

**Förbehåll:** Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från [www.rust-oleum.eu](http://www.rust-oleum.eu) eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)