

Quality Paints since 1845
MATHYS®



MUR-FILLER

Elastic joint filler

- Elastic
- High filling power
- Not sandable (contains quartz)

MUR-FILLER

POPIS PRODUKTU (DLOUHÝ)

Elastic joint filler for reparation of active and non-active cracks, can be used interior and exterior.

DOPORUČENÉ POUŽITÍ

- Repair of joints and cracks on inside and outside walls, for instance: stopping up of active and non-active cracks and joints in masonry, concrete and cement fillings.
- Filling up of joints between masonry and windows or door frames.
- Rejointing of paving tiles on terraces provided there is no stagnating water

TECHNICAL DATA

Hustota (g/cm³): 1,48
Obsah pevných látek v hmotnosti: 79%
Obsah pevných látek v objemu: 69%

DRY TIMES BY 20

Dotykem suché: 16 hours (8 mm wet film thickness)
Suché na manipulaci: 18 hours (8 mm wet film thickness)
Suchý nátěr: Minimum 1 day
Plně vytvrzené: 1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

10 mm (cons.: 15 kg/m²)

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

6,9 mm (cons.: 15 kg/m²)

TEORETICKÁ SPOTŘEBA

- 50 - 60 cm joint length per tube.
- 1 cm joint depth for a joint in V-shape.

PŘÍPRAVA POVRCHU

The cracks to be treated must be opened V-shaped, dusted off and impregnated with Primer 44 HS, with Vernac (diluted with 10% Thinner 22) or with Pegafix.

PODMÍNKY POUŽITÍ

Apply in drying conditions at minimum 5°C.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Cleanup with water.

POZNÁMKY

- Contains quartz, so not appropriated as putty
- Manual spray gun: adapt opening of cartridge to the desired joint width

DATA SAFETY DATA

Úroveň těžkých organických látek: Max. 5 g/l
Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cartridges, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu