

Quality Paints since 1845
MATHYS[®]



MURFILL[®] RENOVATION PAINT

Elastic decorative renovation paint

- > 500 % elastic
- Lasting elasticity till -30°C
- Water vapour permeable
- Matt aspect
- Excellent resistance against aging and contamination

MURFILL® RENOVATION PAINT

POPIS PRODUKTU (DLOUHÝ)

Matt and long-lasting elastic renovation paint. Ideal for renovation and decoration of historical and new buildings.

DOPORUČENÉ POUŽITÍ

Renovation and decoration of exterior walls and façades.

TECHNICAL_DATA

Hustota (g/cm ³):	1,33 - 1,37 (weiss)
Úroveň lesku:	Matt
Obsah pevných látek v hmotnosti:	60 - 63 %
Obsah pevných látek v objemu:	47 - 50 %
Propustnost pro vodní páru:	17g/m ² /24h and Sd (m) = 1,4

DRY_TIMES_BY_20

Dotykem suché:	45 minutes
Suché na manipulaci:	± 8 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	2 days

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

150 µm (cons. : 200 g/m²)

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

70 µm (cons.: 200 g/m²)

TEORETICKÁ SPOTŘEBA

- Normal consumption: min. 400 g/m² (2 coats).
- Application by brush or roller: 200 – 300 g/m² per coat, in function of the application method and the substrate.
- Application by airless: 200 – 500 g/m² per coat, in function of the application method and the substrate.

PRAKTICKÁ SPOTŘEBA

Coverage is theoretical and depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

Substrate must be clean, sound and dry (max. 6% substrate humidity) prior to application.

Remove any moss, algae, etc. with a suitable detergent

Previously painted surfaces (in good condition): apply directly after thorough brushing.

Chalky paints or bare substrates should first be primed with Fixonal or Pegafix. On smooth and non-porous substrates, prime with white Pegalink or with one coat of Noxyde (except white, diluted with 20% of water).

For stain, graffiti blocking and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain.

Cracks < 0,5 mm will be filled with Murfill Renovation Paint. Cracks > 0,5 mm will be filled with Elastofill or Mur-Filler acrylic sealants.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Minimum temperature: 5°C. Max. 80 % R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Use a synthetic brush for application of waterbased products.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Use long nap roller (texture polyamide roller 20 mm) or specific façade roller 24 mm. Depending on the roughness of the substrate.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

If necessary, dilute with 2 - 5% volume water. Nozzle: 13 – 15 / Pressure: 200 bars.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Not possible.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

POZNÁMKY

For any information regarding options of guarantee with this system, please contact Technical Service.

DATA SAFETY DATA

Úroveň těkavých organických látek:	30 g/l max
Kategorie VOC:	A/i
Limitní hodnota VOC:	140 g/l (2007) / 140 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu