

Quality Paints since 1845
MATHYS[®]



MURFILL[®] RENOVATION PAINT

Elastic decorative renovation paint

- > 500 % elastic
- Lasting elasticity till -30°C
- Water vapour permeable
- Matt aspect
- Excellent resistance against aging and contamination

MURFILL® RENOVATION PAINT

BESKRIVNING

Matt and long-lasting elastic renovation paint. Ideal for renovation and decoration of historical and new buildings.

REKOMMENDERAD ANVÄNDNING

Renovation and decoration of exterior walls and façades.

TEKNISK DATA

Densitet:	1,33 - 1,37 (weiss)
Glansnivå:	Matt
Torrsubstansvikt:	60 - 63 %
Torrsubstansvolym:	47 - 50 %
Kondensgenomsläpplighet:	17g/m ² /24h and Sd (m) = 1,4

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	45 minutes
Hanteringstorr:	± 8 hours
Övermålningsbar:	24 hours
Fullt härdad:	2 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

150 µm (cons. : 200 g/m²)

REKOMMENDERAD TORRFILMSTJOCKLEK

70 µm (cons.: 200 g/m²)

TEORETISK FÖRBRUKNING

- Normal consumption: min. 400 g/m² (2 coats).
- Application by brush or roller: 200 – 300 g/m² per coat, in function of the application method and the substrate.
- Application by airless: 200 – 500 g/m² per coat, in function of the application method and the substrate.

PRAKTISK FÖRBRUKNING

Coverage is theoretical and depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

Substrate must be clean, sound and dry (max. 6% substrate humidity) prior to application. Remove any moss, algae, etc. with a suitable detergent

Previously painted surfaces (in good condition): apply directly after thorough brushing. Chalky paints or bare substrates should first be primed with Fixonal or Pegafix. On smooth and non-porous substrates, prime with white Pegalink or with one coat of Noxyde (except white, diluted with 20% of water).

For stain, graffiti blocking and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain.

Cracks < 0,5 mm will be filled with Murfill Renovation Paint. Cracks > 0,5 mm will be filled with Elastofill or Mur-Filler acrylic sealants.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Minimum temperature: 5°C. Max. 80 % R.H.

APPLICERING OCH SPÅDNING: PENSEL

Use a synthetic brush for application of waterbased products.

APPLICERING OCH SPÅDNING: ROLLER

Use long nap roller (texture polyamide roller 20 mm) or specific façade roller 24 mm. Depending on the roughness of the substrate.

APPLICERING OCH SPÅDNING: AIRLESSPRUTA

If necessary, dilute with 2 - 5% volume water. Nozzle: 13 – 15 / Pressure: 200 bars.

APPLICERING OCH SPÅDNING: TRYCKLUFTSSPRUTA

Not possible.

RENGÖRING AV UTRUSTNING/SPILL

Water.

ANMÄRKNINGAR

For any information regarding options of guarantee with this system, please contact Technical Service.

SÄKERHETSDATA

VOC-nivå:	30 g/l max
VOC-kategori:	A/i
VOC-gräns:	140 g/l (2007) / 140 g/l (2010)
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu