

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## MURFILL<sup>®</sup> RP SILOXAN NF

# Hydrophobic, renovate and color in one

- Excellent resistance to aging and pollution
- Self-cleaning, hydrophobic
- Pearly effect
- Water vapor permeable
- Very good coverage

# MURFILL® RP SILOXAN NF

## BESKRIVELSE

Very matt elastic renovation coating for exterior walls based on acrylates-siloxanes.

## ANBEFALT BRUK

Waterproofing of old walls and facades. Resistant against hairline cracks up to 0,2 mm. Protection and renovation of old and new outside walls, micro-fissure grid.

## ANBEFALT SYSTEM

Bare substrates or well conserved undercoats, use Pegaprim Exterior as primer. On powdering substrates which need to be reinforced: prime with MurPrim S NF.

- Smooth, dense substrates: Noxyde diluted with 25% water (cons. 200 g/m<sup>2</sup>)
- Decorative: 1 coat Murfill RP Siloxan NF (cons. 500 g/m<sup>2</sup>)
- Waterproofing: 1 coat Murfill RP Siloxan NF cons. 500 g/m<sup>2</sup>)

## TEKNISKE DATA

Tetthet:	1,40 (depending on colour)
Glansgrad:	Matt
Glansgrad ved 85°:	< 2,0% - at angle of 85 °; very mat.
Tørrestoffinnhold i vekt:	68% (depending on colour)

## TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	4 hours
Håndterbar:	4 -8 hours
Overmalbar:	24 - 48 hours

## TEORETISK FORBRUK

500 g/m<sup>2</sup>

## PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## KLARGJØRING AV OVERFLATE

The substrate must be completely clean, dry and sound. In case of contamination by micro-organisms the substrate must first be cleaned with a fungicide solution.

## BRUKSANVISNING

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

## PÅFØRINGSBETINGELSER

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80%. No condensation during drying time. Low temperatures and/or high relative humidity extend the drying time.

## PÅFØRING & FORTYNNING: PENSEL

Synthetic brushes for water dispersed paints. Do not dilute

## PÅFØRING & FORTYNNING: RULLE

Textured polyamide rollers 20 mm or long haired brushes according to roughness of substrate. Do not dilute.

## RENGJØRING AV UTSTYR/SPILL

Water

## SIKKERHETSDATA

VOC nivå:	40 g/l max.
VOC kategori:	A/c
VOC grense:	40 g/l (2010)
Merknader angående sikkerhet:	Consult safety data sheet and Safety information printed on the can.

## HOLDBARHET

Minimum of 2 years from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

**Tilgjengelige farger & størrelse på forpakninger:** Vennligst referer til den respektive produktsiden på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversikt over tilgjengelige farger og størrelse på forpakninger.

**Ansvarsfraskrivelse:** Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu), eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu