

Quality Paints since 1845
MATHYS®



MURFILL® WATERPROOFING COATING

High build elastic exterior waterproof wall coating

- 400 % Elastic
- Waterproof and water vapour permeable
- Excellent colour retention in exterior atmospheric environment
- Protects reinforced concrete against carbonisation and corrosion
- Can be combined with Murfill® fleece for additional mechanical reinforcement and for bridging of (active) cracks

MURFILL® WATERPROOFING COATING

POPIS PRODUKTU (DLHÝ)

Semi-thick facade coating based on high polymers in water dispersion, waterproof, microporous to vapour and resistant to active cracking. Permanent elasticity of 400%, can be combined with Murfill to bridge joints and active cracks. Provides long-term protection for reinforced concrete against carbonation and rebar corrosion. This protective coating provides exceptional resistance to soiling and atmospheric pollution in rural, urban, maritime and industrial environments. Facades treated with Murfill® are thus protected against water infiltration, masonry splinters and cracks, and natural soiling, to keep buildings looking new and enhance their heritage.

ODPORÚČANÉ POUŽITIE

Coating and waterproofing of walls and façades.

TECHNICAL DATA

Hustota (g/cm ³):	1,33 - 1,37 g/cm ³ (wit)
Úroveň lesku:	Semi-Matt
Úroveň lesku pri 60°:	8-10%
Úroveň lesku pri 85°:	13-16%
Obsah pevných látok v hmotnosti:	60 - 63%
Obsah pevných látok v objeme:	47 - 50%

DRY TIMES BY 20

Na dotyk suché:	45 minutes
Suché na manipuláciu:	± 8 hours
Suchý na opätovné natieranie:	24 hours
Úplne vytvrdené:	± 2 days

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

300 µm (coverage: 400 g/m²)

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

140 µm (coverage: 400 g/m²)

TEORETICKÁ SPOTREBA

- In combination with fleece > 1,3 kg/m².
- 300 - 600 g/m² per coat depending on the application and the substrate.

PRÍPRAVA POVRCHU

Murfill Waterproofing Coating can be applied directly on old (sound) paintwork after thorough brushing down. Chalking paints or substrates must be treated first with Primer 44HS or with Pegafix, when the old paint coat (acrylic paint or Murfill Waterproofing Coating) is affected by the solvents of Primer 44HS. New or unpainted substrates: on porous materials apply first a coat of Primer 44HS or Pegafix. On smooth non-porous substrates apply a coat of Pegalink white or a coat of Noxyde (except for white) diluted with 25% water. For stain, graffiti blocking and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain. Cracks < 0.5 mm wide: fill up with Murfill Waterproofing Coating. Cracks > 0.5 mm wide: fill up with Elastofill or Mur-Filler. Active cracks must be bridged with Murfill fleece.

NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMIENKY APLIKÁCIE

Minimum temperature: 5°C / Maximum 80% R.H.

APLIKÁCIA A RIEDENIE: ŠTETEC

Do not dilute and apply in thick coat.

APLIKÁCIA A RIEDENIE: VALEC

Do not dilute and apply in thick coat.

APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

- If necessary, dilute with 2 - 5% water.
- Nozzle: 18 – 23 / Pressure: 200 bars.

APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Not possible.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Water.

POZNÁMKY

For any information regarding options of guarantee with this system, please contact Technical Service.

DATA SAFETY DATA

Úroveň VOC:	25 g/l max.
Kategória VOC:	A/i
Limit VOC:	140 g/l (2007) / 140 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu