



MURPRIM S

Solvent-based primer with high covering power



- Based on Pliolite
- Impregnates & fixes the mineral substrate
- To be applied on slightly damp surfaces
- Good coverage
- Applicable to recently plastered walls

MURPRIM S

POPIS PRODUKTU (DLOUHÝ)

Solvent-based primer for use in combination with all Mathys façade paints

DOPORUČENÉ POUŽITÍ

Solvent based fixing primer for mineral substrates, old and sound substrates that can be covered with Murfill RP Siloxan, Murfill WP , and for elastic joint filler: Elastofill and Murfiller.

DOPORUČENÝ SYSTÉM

Bare substrate or well conserved undercoats: Murprim Aqua + 400 g/m² MURFILL RP Siloxan or Murfill WP. Old well conserved undercoats must be compatible. Check substrate in advance. Surface irregularities Levelling with repair mortar (Pegacrete) or with filler.

TECHNICAL DATA

Hustota (g/cm³): ± 1,16

Obsah pevných látek v objemu: ± 27 %

Propustnost pro vodní páru: Sd= 0,0031 m (20 µm DFT)

TEORETICKÁ SPOTŘEBA

110 g/m²

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

The substrate must be completely clean, dry and sound and insensitive to water. In case of contamination by micro-organisms the substrate must first be cleaned with a fungicide solution. If the substrate is oily and dirty, this must be cleaned with a solution of Cleaner/degreaser ND14. Remove old not adhering coats.

NÁVOD K POUŽITÍ

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80 %. No condensation during drying time .Low temperatures and/or high relative humidity will extend the drying time.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Natural silk and polyamide.

20 Vol.%white spirit

APLIKACE A ŘEDĚNÍ: VÁLEČEK

12 mm or long haired brushes according to roughness of substrate.

20 Vol.% white spirit

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLÍTÍ

White spirit or Thinner Rust Oleum 160

DATA_SAFETY_DATA

Úroveň těkavých organických

látek: 749 g/l max

Kategorie VOC: A/h

Limitní hodnota VOC: 750 g/l (2010)

Poznámky k bezpečnosti: Consult safety data sheet and Safety information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu