

Quality Paints since 1845
MATHYS[®]



MURPRIM S

Solvent-based primer with high covering power

- Based on Pliolite
- Impregnates & fixes the mineral substrate
- To be applied on slightly damp surfaces
- Good coverage
- Applicable to recently plastered walls



MURPRIM S

BESKRIVELSE

Solvent-based primer for use in combination with all Mathys façade paints

ANBEFALT BRUK

Solvent based fixing primer for mineral substrates, old and sound substrates that can be covered with Murfill RP Siloxan, Murfill WP, and for elastic joint filler: Elastofill and Murfiller.

ANBEFALT SYSTEM

Bare substrate or well conserved undercoats: Murprim Aqua + 400 g/m² MURFILL RP Siloxan or Murfill WP. Old well conserved undercoats must be compatible. Check substrate in advance. Surface irregularities Levelling with repair mortar (Pegacrete) or with filler.

TEKNISKE DATA

Tetthet: ± 1,16
Tørrestoffinnhold i volum: ± 27 %
Vanndampermeabilitet: Sd= 0,0031 m (20 µm DFT)

TEORETISK FORBRUK

110 g/m²

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

The substrate must be completely clean, dry and sound and insensitive to water. In case of contamination by micro-organisms the substrate must first be cleaned with a fungicide solution. If the substrate is oily and dirty, this must be cleaned with a solution of Cleaner/degreaser ND14. Remove old not adhering coats.

BRUKSANVISNING

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80 %. No condensation during drying time. Low temperatures and/or high relative humidity will extend the drying time.

PÅFØRING & FORTYNNING: PENSEL

Natural silk and polyamide.

20 Vol.%white spirit

PÅFØRING & FORTYNNING: RULLE

12 mm or long haired brushes according to roughness of substrate.
20 Vol.% white spirit

RENGJØRING AV UTSTYR/SPILL

White spirit or Thinner Rust Oleum 160

SIKKERHETSDATA

VOC nivå: 749 g/l max
VOC kategori: A/h
VOC grense: 750 g/l (2010)
Merknader angående sikkerhet: Consult safety data sheet and Safety information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu