

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## MURPRIM S

# Solvent-based primer with high covering power

- Based on Pliolite
- Impregnates & fixes the mineral substrate
- To be applied on slightly damp surfaces
- Good coverage
- Applicable to recently plastered walls



# MURPRIM S

## POPIS PRODUKTU (DLHÝ)

Solvent-based primer for use in combination with all Mathys façade paints

## ODPORÚČANÉ POUŽITIE

Solvent based fixing primer for mineral substrates, old and sound substrates that can be covered with Murfill RP Siloxan, Murfill WP, and for elastic joint filler: Elastofill and Murfiller.

## ODPORÚČANÝ SYSTÉM

Bare substrate or well conserved undercoats: Murprim Aqua + 400 g/m<sup>2</sup> MURFILL RP Siloxan or Murfill WP. Old well conserved undercoats must be compatible. Check substrate in advance. Surface irregularities Levelling with repair mortar (Pegacrete) or with filler.

## TECHNICAL DATA

Hustota (g/cm<sup>3</sup>): ± 1,16  
Obsah pevných látok v objeme: ± 27 %  
Priepustnosť vodnej pary: Sd= 0,0031 m (20 µm DFT)

## TEORETICKÁ SPOTREBA

110 g/m<sup>2</sup>

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PRÍPRAVA POVRCHU

The substrate must be completely clean, dry and sound and insensitive to water. In case of contamination by micro-organisms the substrate must first be cleaned with a fungicide solution. If the substrate is oily and dirty, this must be cleaned with a solution of Cleaner/degreaser ND14. Remove old not adhering coats.

## NÁVOD NA POUŽITIE

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

## PODMIENKY APLIKÁCIE

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80 %. No condensation during drying time. Low temperatures and/or high relative humidity will extend the drying time.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Natural silk and polyamide.

20 Vol.% white spirit

## APLIKÁCIA A RIEDENIE: VALEC

12 mm or long haired brushes according to roughness of substrate.  
20 Vol.% white spirit

## ČISTENIE ZARIADENIA / POSTRIEKANIE

White spirit or Thinner Rust Oleum 160

## DATA SAFETY DATA

Úroveň VOC: 749 g/l max  
Kategória VOC: A/h  
Limit VOC: 750 g/l (2010)  
Poznámky k bezpečnosti: Consult safety data sheet and Safety information printed on the can.

## SKLADOVATELNOSŤ

Minimum of 2 years from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu