

Quality Paints since 1845
MATHYS[®]



MURPRIM S

Solvent-based primer with high covering power

- Based on Pliolite
- Impregnates & fixes the mineral substrate
- To be applied on slightly damp surfaces
- Good coverage
- Applicable to recently plastered walls



MURPRIM S

BESKRIVNING

Solvent-based primer for use in combination with all Mathys façade paints

REKOMMENDERAD ANVÄNDNING

Solvent based fixing primer for mineral substrates, old and sound substrates that can be covered with Murfill RP Siloxan, Murfill WP , and for elastic joint filler: Elastofill and Murfiller.

REKOMMENDERAT SYSTEM

Bare substrate or well conserved undercoats: Murprim Aqua + 400 g/m² MURFILL RP Siloxan or Murfill WP. Old well conserved undercoats must be compatible. Check substrate in advance. Surface irregularities Levelling with repair mortar (Pegacrete) or with filler.

TEKNISK DATA

Densitet: ± 1,16
Torrsubstansvolym: ± 27 %
Kondensgenomsläpplighet: Sd= 0,0031 m (20 µm DFT)

TEORETISK FÖRBRUKNING

110 g/m²

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

The substrate must be completely clean, dry and sound and insensitive to water. In case of contamination by micro-organisms the substrate must first be cleaned with a fungicide solution. If the substrate is oily and dirty, this must be cleaned with a solution of Cleaner/degreaser ND14. Remove old not adhering coats.

BRUKSANVISNING

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80 %. No condensation during drying time .Low temperatures and/or high relative humidity will extend the drying time.

APPLICERING OCH SPÄDNING: PENSEL

Natural silk and polyamide.

20 Vol.%white spirit

APPLICERING OCH SPÄDNING: ROLLER

12 mm or long haired brushes according to roughness of substrate.
20 Vol.% white spirit

RENGÖRING AV UTRUSTNING/SPILL

White spirit or Thinner Rust Oleum 160

SÄKERHETSDATA

VOC-nivå: 749 g/l max
VOC-kategori: A/h
VOC-gräns: 750 g/l (2010)
Anmärkningar om säkerhet: Consult safety data sheet and Safety information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu