

Quality Paints since 1845
MATHYS[®]



PARACEM[®] SEMI-MATT

Acrylic exterior wall paint with high covering power



- High durability
- Perfect saponification resistance
- Particularly high covering capacity
- Sufficiently breathing (water vapour permeable)
- Hardly permeable to rain Excellent weather resistance

PARACEM® SEMI-MATT

POPIS PRODUKTU (DLOUHÝ)

- Acrylic exterior wall paint with high covering power
- Acrylic paint for outside and inside use

DOPORUČENÉ POUŽITÍ

For old or new substrates like masonry, cement rendering or plaster, concrete, tiles, plaster boards and wooden panels.

TECHNICAL DATA

Hustota (g/cm ³):	1,5
Úroveň lesku:	Semi-Matt
Úroveň lesku při 60°:	5%
Obsah pevných látek v hmotnosti:	64%
Obsah pevných látek v objemu:	46%
Propustnost pro vodní páru:	23g/m ² /24h and Sd (m) = 1,0

DRY TIMES BY 20

Dotykem suché:	40 minutes (10 m ² /l)
Suché na manipulaci:	2 hours (10 m ² /l)
Suchý nátěr:	4 hours (10 m ² /l)
Plně vytvrzené:	1 day

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 micron (cons.: 10 m²/l)

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

45 micron (cons.: 10 m²/l)

TEORETICKÁ SPOTŘEBA

7 - 10 m²/l per coat

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

The substrate must be sufficiently dry and stable; clean thoroughly. In case of fungal growth: treat first with an adequate moss-preventing product. On porous substrates apply first a coat of Parafix or Pegafix / Paracem (25 / 75). On very smooth bricks, apply a first coat of Noxyde diluted with 25% water, or a coat of Pegalink. Impregnate old chalking paints, after cleaning, with a coat of Fixonal or Pegafix. For stain, graffiti blocking and/or very fast recoating on all substrates, for interior or exterior, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain. Fill up holes and seal joints or fissures with Elastofill. If necessary, fill with Pegaflex. Flat down and remove dust. Hereafter, apply 1 - 2 coats of Paracem.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Minimum 5C / Maximum 80 % R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply with flat brush

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply with dispersion roller.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 013 - 018 / Pressure: 180 bars.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Dilute with water (3 - 5% volume).

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Water.

DATA SAFETY DATA

Úroveň těkavých organických látek:	25 g/l max.
Kategorie VOC:	A/c
Limitní hodnota VOC:	75 g/l (2007) / 40 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu