



PARACEM[®] DECO MATT

High-quality matt interior wall paint

- Excellent flow
- Good mechanical resistance against rubbing
- Smooth mat aspect
- High covering power
- Tendency not to overlap

PARACEM® DECO MATT

POPIS PRODUKTU (DLOUHÝ)

Decorative and matt finishing for indoor walls and ceilings. Applicable on most substrates (plaster, bricks, concrete, etc.) as well in private as in public buildings.

DOPORUČENÉ POUŽITÍ

Decorative and matt finishing for indoor walls and ceilings. Applicable on most substrates (plaster, bricks, concrete, etc.) as well in private as in public buildings.

TECHNICAL DATA

Hustota (g/cm ³):	1,38 - 1,4 (white)
Úroveň lesku:	Matt
Úroveň lesku při 60°:	Matt: 2-3%
Úroveň lesku při 85°:	Matt: 2-3%
Obsah pevných látek v hmotnosti:	50,5 - 52,5% (white)
Obsah pevných látek v objemu:	33 - 35% (white)
Odolnost proti drhnutí za mokra (EN 13300):	wsr_c1

DRY TIMES BY 20

Dotykem suché:	30 minutes
Suchý nátěr:	1 hour
Plně vytvrzené:	2 days

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

140 µm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

50 µm

TEORETICKÁ SPOTŘEBA

7 - 10 m²/l per coat

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

PŘÍPRAVA POVRCHU

The surface must be dry and free of dust and grease. You can paint Paracem® Deco Matt directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous. You must treat porous surfaces with Paracem® Deco Primer first. Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first. Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus. Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus). Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123. On glass fibre, apply preferably first a coat of Paracem® Deco Primer or Zinsser primers Bulls Eye 123 or 123 Plus before finishing with 2 coats of Paracem® Deco Matt.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Apply undiluted.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Apply undiluted.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 013 - 019 / Pressure: 160 - 200 bars

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Possible. If necessary dilute with water.

APLIKACE A ŘEDĚNÍ: AEROSOL

> 5°C, < 80% R.H.

DATA SAFETY DATA

Úroveň těkavých organických látek:	30 g/l
VOC readymix:	30 g/l
Kategorie VOC:	A/a
Limitní hodnota VOC:	30 g/l

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu