



PARACEM[®] DECO MATT

High-quality matt interior wall paint

- Excellent flow
- Good mechanical resistance against rubbing
- Smooth mat aspect
- High covering power
- Tendency not to overlap

PARACEM® DECO MATT

BESKRIVELSE

Decorative and matt finishing for indoor walls and ceilings. Applicable on most substrates (plaster, bricks, concrete, etc.) as well in private as in public buildings.

ANBEFALT BRUK

Decorative and matt finishing for indoor walls and ceilings. Applicable on most substrates (plaster, bricks, concrete, etc.) as well in private as in public buildings.

TEKNISKE DATA

Tetthet:	1,38 - 1,4 (white)
Glansgrad:	Matt
Glansgrad ved 60°:	Matt: 2-3%
Glansgrad ved 85°:	Matt: 2-3%
Tørrstoffinnhold i vekt:	50,5 - 52,5% (white)
Tørrstoffinnhold i volum:	33 - 35% (white)
wet_scrub_resistance:	wsr_c1

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	30 minutes
Overmalbar:	1 hour
Herdetid:	2 days

ANBEFALT VÅTFILMTYKKELSE

140 µm

ANBEFALT TØRRFILMTYKKELSE

50 µm

TEORETISK FORBRUK

7 - 10 m²/l per coat

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

KLARGJØRING AV OVERFLATE

The surface must be dry and free of dust and grease. You can paint Paracem® Deco Matt directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous. You must treat porous surfaces with Paracem® Deco Primer first. Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first. Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus. Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus). Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123. On glass fibre, apply preferably first a coat of Paracem® Deco Primer or Zinsser primers Bulls Eye 123 or 123 Plus before finishing with 2 coats of Paracem® Deco Matt.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRING & FORTYNNING: PENSEL

Apply undiluted.

PÅFØRING & FORTYNNING: RULLE

Apply undiluted.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 013 - 019 / Pressure: 160 - 200 bars

PÅFØRING & FORTYNNING: FORSTØVNINGS-SPRØYTE

Possible. If necessary dilute with water.

PÅFØRING & FORTYNNING: AEROSOL

> 5°C, < 80% R.H.

SIKKERHETSDATA

VOC nivå:	30 g/l
VOC ferdigblandet:	30 g/l
VOC kategori:	A/a
VOC grense:	30 g/l

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukeren er selv ansvarlig for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu