



## PARACEM<sup>®</sup> DECO MATT

# High-quality matt interior wall paint

- Excellent flow
- Good mechanical resistance against rubbing
- Smooth mat aspect
- High covering power
- Tendency not to overlap

# PARACEM® DECO MATT

## POPIS PRODUKTU (DLHÝ)

Decorative and matt finishing for indoor walls and ceilings. Applicable on most substrates (plaster, bricks, concrete, etc.) as well in private as in public buildings.

## ODPORÚČANÉ POUŽITIE

Decorative and matt finishing for indoor walls and ceilings. Applicable on most substrates (plaster, bricks, concrete, etc.) as well in private as in public buildings.

## TECHNICAL DATA

Hustota (g/cm <sup>3</sup> ):	1,38 - 1,4 (white)
Úroveň lesku:	Matt
Úroveň lesku pri 60°:	Matt: 2-3%
Úroveň lesku pri 85°:	Matt: 2-3%
Obsah pevných látok v hmotnosti:	50,5 - 52,5% (white)
Obsah pevných látok v objeme:	33 - 35% (white)
Odolnosť voči mokrému drhnutiu (EN 13300):	wsr_c1

## DRY TIMES BY 20

Na dotyk suché:	30 minutes
Suchý na opätovné natieranie:	1 hour
Úplne vytvrdené:	2 days

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

140 µm

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

50 µm

## TEORETICKÁ SPOTREBA

7 - 10 m<sup>2</sup>/l per coat

## PRAKTICKÁ VÝDATNOSŤ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

## PRÍPRAVA POVRCHU

The surface must be dry and free of dust and grease. You can paint Paracem® Deco Matt directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous. You must treat porous surfaces with Paracem® Deco Primer first. Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first. Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus. Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus). Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123. On glass fibre, apply preferably first a coat of Paracem® Deco Primer or Zinsser primers Bulls Eye 123 or 123 Plus before finishing with 2 coats of Paracem® Deco Matt.

## NÁVOD NA POUŽITIE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APLIKÁCIA A RIEDENIE: ŠTETEC

Apply undiluted.

## APLIKÁCIA A RIEDENIE: VALEC

Apply undiluted.

## APLIKÁCIA A RIEDENIE: BEZVZDUCHOVÉ STRIEKANIE

Nozzle: 013 - 019 / Pressure: 160 - 200 bars

## APLIKÁCIA A RIEDENIE: VZDUCHOVO ATOMIZOVANÝ SPREJ

Possible. If necessary dilute with water.

## APLIKÁCIA A RIEDENIE: AEROSÓL

> 5°C, < 80% R.H.

## DATA SAFETY DATA

Úroveň VOC:	30 g/l
VOC readymix:	30 g/l
Kategória VOC:	A/a
Limit VOC:	30 g/l

## SKLADOVATEĽNOSŤ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu